

## European Technical Assessment

**ETA-08/0178**  
**of 26.10.2023**

### General Part

**Technical Assessment Body issuing the European Technical Assessment**

SINTEF AS by its institute SINTEF Community

**Trade name of the construction product**

Kodumaja Building modules

**Product family to which the construction product belongs**

34: Structural Timber Product Elements and Ancillaries Timber frame building kits

**Manufacturer**

Kodumaja AS  
Puidu 2  
Tartu 50411  
Estonia  
<http://www.kodumaja.ee>

**Manufacturing plant(s)**

KM Element OÜ  
Factory 1: Puidu 2, Tartu 50411, Estonia  
Factory 2: Betooni 2, Tartu 50411, Estonia

**This European Technical Assessment contains**

54 pages including 2 Annexes which form an integral part of this assessment

Annex B contains confidential information and is not included in the European Technical Assessment when that assessment is publicly disseminated

**This European Technical Assessment is issued in accordance with Regulation (EU) No 305/2011, on the basis of**

EAD 340308-00-0203 Timber Building Kits

**This version is a corrigendum of**

ETA 08/0178, version 3, issued on 26/10/2023

Translations of this European Technical Assessment in other languages shall fully correspond to the original issued document and should be identified as such.

Communication of this European Technical Assessment, including transmission by electronic means, shall be in full (excepted the confidential Annex(es) referred to above). However, partial reproduction may be made, with the written consent of the issuing Technical Assessment Body. Any partial reproduction has to be identified as such.

## 1. Technical description of the product

The purpose of this assessment of Kodumaja AS is to obtain a European Technical Assessment (ETA) for building kits of prefabricated building modules with the following trade name: “Kodumaja Building modules”. The kit is recognized as a construction product within the product area “Building Kits, Units, and Prefabricated Elements” – product area code (PAC) 34, according to the Construction Product Regulation (EU) No 305/2011 (CPR). Henceforth within the document, the kit shall be referred to as, “Kodumaja Building modules”.

The Kodumaja building modules are kits made of prefabricated building modules with timber frame structures in floors, walls and roof. The basic design of wall, floor and roof constructions, including the detailed design specifications (connections between components / elements and assembly details) are presented in Annex A1 and Annex B<sup>1</sup>. The material and component specifications are given in Annex A2, Table A2-1 of this ETA.

Module size is custom made for each delivery, but maximum dimensions are 5.3 m width, 3.8 m height and 14.5 m length.

This assessment covers the standard design of the module structures ie. external and internal walls, floors and roofs, including external envelope with timber cladding and fibre cement boards, the wet rooms, and the connections between several modules installed together as a building.

The assessment does not cover foundations of the building, external or internal surface finishes, windows, doors, roofing materials such as roof tiles, supplementary components like stairs, balconies etc., or technical service installations for water, heating and ventilation systems. These products are specified case by case, and their performance have to be verified specifically as parts of the works in each case.

The modules shall be installed according to the relevant construction details in Annex B, together with a special installation manual worked out by the manufacturer for each individual works. The installation manual shall cover all installation aspects for the modules, including erection systems and equipment, temporary bracing, permanent anchoring to foundations and between modules, weather protection during installation, materials and components which are necessary supplements to the modules as well as standard assembly joints and special joint designs for individual modules.

The modules shall be fully protected from weather exposure and mechanical damage during storage, transportation and installation.

Package, transport, storage, erection and maintenance of the kits are laid down in manufacturer technical documentation.

---

<sup>1</sup> Annex B contains confidential information and is not included in the European Technical Assessment when that assessment is publicly disseminated.

## **2. Specification of the intended use(s) in accordance with the applicable European Assessment Document (hereinafter EAD)**

“Kodumaja building modules” are intended for low rise or multi-storey houses, with vertical and horizontal separations between housing units and within the limitations of the regulations valid on the place of use. The modules may also be used for non-residential buildings where the performance requirements are more or less the same as for residential houses.

The intended use shall be evaluated for each individual case depending on the climatic and geographic conditions.

The modules are designed to accommodate climatic conditions where humidity predominantly flows from the building's interior to its exterior for a major part of the year. This essential aspect should be taken into careful consideration when deploying the building kits in the southern regions of Europe.

The kits are intended to be placed on all types of ordinary foundations like concrete slabs on ground, masonry or concrete basement walls, or strip foundations. The modules shall be placed on a foundation that meets the manufacturer's specified requirements concerning dimensions, tolerances ( $\pm 3$  mm) and loadbearing capacity. A damp-proof course or equivalent must prevent moisture uptake in the modules from foundations.

No special assessment of structural resistance related to seismic actions has been performed.

The use of kit in regions where termite attack can occur is impermissible without additional chemical treatment.

The provisions made in this ETA are based on an assumed working life of 50 years for load bearing and non-accessible construction components and materials, and 25 years for repairable or replaceable components and materials, provided that building kits are subject to appropriate installation, use and maintenance. The indications given on the working life cannot be interpreted as a guarantee given by the producer but are to be regarded only as a means for choosing the right products in relation to the expected economically reasonable working life of the works.

The design process and complete works must comply with the procedures foreseen in the Member State in which the building kit will be erected.

### 3. Performance of the product and references to the methods used for its assessment

The assessment is performed according to EAD 340308-00-0203, Timber Building Kits edition January 2019. The latest release of all referenced standards should always be taken into consideration. Product characteristics used in calculations are based on proved data provided by producers or by appropriate standard. Relevance of defined product characteristics is related to validity of standard / reports used in preparation of ETA.

Table 1 shows the characteristics for which the product performances are declared in this ETA. The characteristics correspond to the Kodumaja building modules design specified in Annex A1 and B.

Table 1 Performance of the product

<b>Product name: Kodumaja building modules</b>		<b>Intended use:</b> Low rise and multi-storey residential, institutional, commercial, and industrial buildings	
<b>Basic Work Requirements (BWR)</b>	<b>Essential characteristics of construction product</b>	<b>Assessment method</b>	<b>Product performance</b>
BWR 1: Mechanical resistance and stability	Resistance, stiffness and stability of wall, floor and roof elements and their connections against vertical and horizontal loads	Clause 3.1.1	See cl. 3.1.1 and Annex A1 and Annex A2, Table A2-1
	Shear resistance in plane direction against horizontal loads	Clause 3.1.2	No performance assessed (NPA)
	Corrosion protection of metal fasteners	Clause 3.1.3	Clause 3.1.3 and Annex A2, Table A2-2
BWR 2: Safety in case of fire	Reaction to fire	Clause 3.2.1	See cl. 3.2.1 and Annex A2 Table A2-1
	Fire resistance	Clause 3.2.2	See cl. 3.2.2 and Annex A3 Table A3-1
	External fire performance of roof covering	Clause 3.2.3	See cl. 3.2.3
BWR 3: Hygiene, health and the environment	Vapour permeability and moisture resistance	Clause 3.3.1	See cl. 3.3.1
	Watertightness <ul style="list-style-type: none"> <li>• External envelope</li> <li>• Internal surfaces</li> </ul>	Clause 3.3.2.1 Clause 3.3.2.2	See cl. 3.3.2.1 See cl. 3.3.2.2
	Durability class / Use class	Clause 3.3.3	See cl. 3.3.3
	Content and release of dangerous substances	Clause 3.3.4	No performance assessed (NPA)

<b>Product name: Kodumaja building modules</b>		<b>Intended use:</b> Low rise and multi-storey residential, institutional, commercial, and industrial buildings	
<b>Basic Work Requirements (BWR)</b>	<b>Essential characteristics of construction product</b>	<b>Assessment method</b>	<b>Product performance</b>
BWR 4: Safety and accessibility in use	Impact resistance	See cl. 3.4.1	See cl. 3.4.1
BWR 5: Protection against noise	Airborne sound insulation of walls, floors and roof structures	See cl. 3.5.1	See cl. 3.5.1 and Annex A1
	Impact sound insulation of floors	See cl. 3.5.2	See cl. 3.5.2 and Annex A1
	Sound absorption	See cl. 3.5.3	No performance assessed (NPA)
BWR 6: Energy economy and heat retention	Thermal resistance	See cl. 3.6.1	See cl. 3.6.1 and Annex A4 Table A4-1.
	Air permeability	See cl. 3.6.2	See cl. 3.6.2
	Thermal inertia	See cl. 3.6.3	No performance assessed (NPA)
BWR 7: Sustainable use of natural resources	Sustainable use of natural resources	See cl. 3.7	No performance assessed (NPA)

### **3.1 Mechanical resistance and stability (BWR 1)**

#### **3.1.1 Resistance, stiffness and stability of wall, floor and roof elements and their connections against vertical and horizontal loads**

Indication of geometrical data of the components and elements and their properties related to mechanical resistance and stability are used as an expression of resistance, stiffness and stability of wall, floor and roof elements and their connections against vertical and horizontal loads.

The components of the kit - wall, floor and roof elements - are listed in Annex A1 and described with regard to their composition, including relevant fasteners for their assembling and for connections between components. Detailed material specifications (components and fasteners) are given in Annex Annex A2, Table A2-1. Typical connection details between the components are given in Annex B.

Information given are used for case-by-case calculations according EN 1990, EN 1991, EN 1995-1-1 and EN 1998-1 taking into consideration respective requirements of the Member States regarding ultimate limit state and serviceability limit state.

#### **3.1.2 Shear resistance in plane direction against horizontal loads**

No performance assessed (NPA) option is applied.

### **3.1.3 Corrosion protection of metal fasteners**

Corrosion protection of metal fasteners corresponds to the requirements of the intended service class according to EN 1995-1-1 (Service Classes 1-3) and it is expressed as Service class, material type (stainless steel) or as type / thickness of corrosion protection (zinc coating). Corrosion protection of metal fasteners is given in Annex A2, Table A2-2.

## **3.2 Safety in case of fire (BWR 2)**

### **3.2.1 Reaction to fire**

Reaction to fire classification according to EN 13501-1+A1 is shown for each individual material and component in Annex A2.

A European reference fire scenario has not been established for facades. In some Member States, a classification according to EN 13501-1 might not be sufficient for the use in facades. An additional assessment of Kodumaja building modules according to national provisions (e.g. on the basis of a large scale fire test) might be necessary to comply with Member State regulations, until a European classification system has been completed.

### **3.2.2 Fire resistance**

For basic module designs, as shown in the Annex A1, the resistance to fire classified according to EN 13501-2+A1 is tabulated in Annex 3, table A3-1.

For alternative module design, as shown in Annex B only, the resistance to fire classified according to EN 13501-2+A1 is tabulated in Annex 3, table A3-2.

### **3.2.3 External fire performance of roof covering**

The roof covering shall be tested using the test method relevant for the corresponding external fire performance roof class and classified according to EN 13501-5.

Reaction to fire classification for roof covering is shown in Annex A2, table A2-1.

## **3.3 Hygiene, health and the environment (BWR 3)**

### **3.3.1 Vapour permeability and moisture resistance**

Vapour permeability and moisture resistance of the module construction using the material properties defined in Annex A2, have been assessed on the basis of calculations according to EN ISO 13788 to be acceptable for the intended use indicated in clause 2. The overall design of the kit's external envelope has been assessed to provide adequate moisture control for the intended use.

For the areas where the climate requires (e.g. in regions with high external temperature and/or high vapour pressure), or cooling systems are installed and used for longer periods, the kit should not be used unless the risk of moisture condensation has been assessed for each individual works (EN ISO 13788).

### **3.3.2 Watertightness**

#### *3.3.2.1 External envelope*

The typical design of the external envelope structures in "Kodumaja building modules" consists of well-known technical solutions and has been assessed on the basis of engineering judgement and relevant

experience<sup>2</sup> to give adequate watertightness against rain, driving rain and snow exposure in general. The watertightness of the external envelope has been assessed on the basis of the standard construction details as shown in Annex B. The kit elements are designed according to the two-stage principle.

### 3.3.2.2 *Internal surfaces*

The membrane system used to provide watertightness of zones with direct water exposure in internal wet room floors and walls has been tested and assessed according to the provisions in EAD 030352-00-0503 Watertight covering kits for wet room floors and/or walls.

The floors and walls classified as watertight face areas are shown in Annex 1, and membrane systems used in the kit are given in Annex 2, table A2-1.

### 3.3.3 **Durability class / Use class**

The timber species used in the modules are softwood in class 4 concerning natural durability and resistance to fungus attack according to EN 350-2. Structural components and internal linings are in hazard class 1 according to EN 335-1, and timber cladding is in hazard class 2.

Durability of wood-based panels is according to EN 13986 expressed as EN 335 Use Class (1 or 2).

Based on assessment of typical construction details, wood-based materials exposed to external climate have ability to dry between wetting periods.

### 3.3.4 **Content and release of dangerous substances**

No performance assessed (NPA) option is applied.

Note: Manufacturer declares that only timber-based products with formaldehyde class E1 and wood-based panels with release of pentachlorophenol  $\leq 5$  ppm, are used.

## 3.4 **Safety and accessibility in use**

### 3.4.1 **Impact resistance**

Impact resistance of module walls is assessed as adequate as well-known internal lining materials (OSB/3, gypsum fibre / plasterboards) with thickness ( $t \geq 10$  mm) and stud spacing ( $\leq 0.65$  m) are used in element composition.

This deemed to satisfy the conditions of EAD 340308-00-00203, Clause 2.2.13.

## 3.5 **Protection against noise**

### 3.5.1 **Airborne sound insulation of walls, floors and roof structures**

Estimated weighted apparent airborne sound reduction index  $R'w$  (C; Ctr) (dB) for standard separating wall and floor constructions between housing units as defined in ISO 140/ISO 717 is  $R'w(C; Ctr) \geq 55$  dB.

No performance has been assessed for the roof constructions.

Values can be verified by on-site testing of completed structures.

---

<sup>2</sup> Knut Ivar Edvardsen og Trond Ramstad SINTEF Byggforsk (2014): Trehus Håndbok 5, Oslo ISBN 978-82-536-1391-8

### **3.5.2 Impact sound insulation of floors**

Impact sound insulation performance for the typical floor constructions, as described in Annex A1 and annex B is verified on basis of estimated values of impact sound insulation expressed as weighted normalised impact sound pressure  $L'_{n,w}$  (CI) (dB) (band with 1/3 octave) according to EN ISO 717-2.

Performance value determined for the standard separating floor construction between housing units in "Kodumaja Building Modules" is  $L'_{n,w}$  (CI)  $\leq$  53 dB.

Values can be verified by on-site testing of completed structures.

No performance has been assessed for the roof constructions.

### **3.5.3 Sound absorption**

No performance assessed (NPA) option is applied.

## **3.6 Energy economy and heat retention**

### **3.6.1 Thermal resistance**

According to EN ISO 6946 thermal resistance is calculated as thermal resistance  $R_T$  and as corresponding thermal transmittance  $U_a$ , see table for actual construction in Annex A1. Thermal conductivities of insulation materials as declared in declaration of performance (DoP), are used in thermal calculations.

### **3.6.2 Air permeability**

The assessment of air permeability in the external envelope is based on the examination of joints between various components within the kit and connections between the kit and other building elements. To ensure airtightness, foil overlapping is employed at these joints, utilizing methods such as clamping and the application of tape.

Standard construction details of the kit presented in the Annex A1 and B have been assessed to have adequate air tightness for the specified intended use based on the judgement of the construction details on the basis of the knowledge and experience.<sup>3</sup>

### **3.6.3 Thermal inertia**

No performance assessed (NPA) option is applied.<sup>4</sup>

## **3.7 Sustainable use of natural resources**

No performance assessed (NPA) option is applied.

---

<sup>3</sup> Knut Ivar Edvardsen og Trond Ramstad SINTEF Byggforsk (2014): Trehus Håndbok 5, Oslo ISBN 978-82-536-1391-8

<sup>4</sup> Values for properties such as density, specific heat capacity, and thermal resistance of the relevant component are provided in Annex A2, Table A2-1. This information aids the designer in calculating the thermal inertia of the building for each building kit, also when it is required by relevant national legislation at intended building place.



**4. Assessment and verification of constancy of performance (hereinafter AVCP) system applied, with reference to its legal base**

According to the Decision 1999/455/EU of the European Commission, the system of assessment and verification of constancy of performance (see Annex V of Regulation (EU) No 305/2011) to be applied is system 1.

**5. Technical details necessary for the implementation of the AVCP system, as provided for in the applicable EAD**

All relevant technical details necessary for the implementation of the AVCP system are laid down in the Control Plan<sup>5</sup> deposited at SINTEF AS.

Issued in Oslo on 26.10.2023

By

SINTEF AS by its institute SINTEF Community



Anne-Jorunn Enstad

Certification Manager

**Annexes**

Annex A1 – Basic module design/ building elements

Annex A2 – Material and component specifications

Annex A3 – Resistance to fire

Annex B – Standard construction details (separate document, not included)

---

<sup>5</sup> The control plan is a confidential part of this European Technical Assessment and only handed over to the notified body involved in the procedure of attestation and verification and constancy of performance.

## **ANNEX A1**

Index of building elements:

- 1 External wall – type EW-01
- 2 External wall (wet-room) – type EW-01-W
- 3 External wall – type EW-02
- 4 External wall (wet-room) – type EW-02-W
- 5 External wall – type EW-03
- 6 External wall (wet-room) – type EW-03-W
- 7 Internal wall – type IW-01
- 8 Internal wall (wet-room) – type IW-01-W
- 9 Load bearing separating wall – type PW-01
- 10 Load bearing separating wall (wet-room) – type PW-01-W
- 11 Intermediate storey partition floor – type CE-01
- 12 Intermediate storey partition floor (wet-room) – type CE-02
- 13 Floor – type FE-01
- 14 Floor – type FE-02
- 15 Floor (wet-room)– type FE-03
- 16 Floor (wet-room)– type FE-04
- 17 Roof (sloped) RE-01
- 18 Roof (flat) RE-02

1 External wall – type EW-01

**Building Element**

**Wall cross section:**

**Building physics characteristics:**

Thermal resistance<sup>1)</sup> (Ch. 3.3.1):

D <sub>insulation</sub> [mm]	Mineral glass wool	
	U [W/m <sup>2</sup> K]	R [m <sup>2</sup> K/W]
95+95	0.21	4.74
95+120	0.19	5.30
95+145	0.17	5.84
95+170	0.16	6.39
95+195	0.14	6.92

<sup>1)</sup> Values given are valid for internal substrates A  
Values are based on 15% timber proportion in layer 4 and 6

Vapour permeability and moisture resistance (Ch. 3.3.1):  
no condensation

Airborne sound insulation (Ch. 3.5.1):  
R<sub>w</sub> (C<sub>v</sub>) ≥ 50 (-2; -7) db

**Element composition (from outside to inside):**

Nr	Building material	Type	Dimensions [mm]	Spac. / Dist. [mm]
1	External layers (see External layers table)			
2	Wind-barrier gypsum plasterboard	EH / GM-H; A2-s1,d0	≥ 9	-
3	Thermal insulation: Mineral glass wool	λ <sub>0</sub> =0,035 W/mK; A1	95/120/145/170/195	-
4	Solid timber frame	C24	45/95 (120,145,170,195)	e ≤ 600
5	Timber based boards	OSB/3	9	-
6	Thermal insulation: Mineral glass wool	λ <sub>0</sub> =0,035 W/mK; A1	95	-
7	Solid timber frame	C24	45/95	e ≤ 600
	Vapour barrier (between plasterboards, not in wet rooms)	S <sub>d</sub> ≥ 40; F	≥ 0.15	-
	Internal substrates (see Internal substrates layers table)			

**Fasteners:**


Nr	Building material	Type / Dimensions [mm]	Spac. / Dist. [mm]	
			Edge	Middle
2	Wind-barrier gypsum plasterboard	According to producer manual	According to producer manual	
3/5	Solid timber frame	Nail 3.1x90	min. 2pcs/joint	
4	Timber based boards (OSB/3)	Nail 2.5x50	≤ 100	≤ 100

**External layers**

	Building materials	Type	Dimensions [mm]	Spac. / Dist.[mm]
A	Vertical timber laths	Solid timber	30/70	e ≤ 600
	Horizontal timber cladding	Solid timber	≥19	
B	Vertical timber laths	Solid timber	30/70	e ≤ 600
	Horizontal timber laths	Solid timber	30/45	e ≤ 600
	Vertical timber cladding	Solid timber	≥19	
C	Vertical timber laths	Solid timber	30/70 (95)	e ≤ 600
	Fibre-cement boards	A2-s1,d0	≥8	


**Fasteners:**



Building material	Type / Dimensions [mm]	Spac. / Dist. [mm]	
		Edge	Middle
Timber laths	Nail 3.1x90 / 3.8x130	2 pcs/joint	
Timber cladding	Nail 2.5x50	min. 1 pcs/joint	
Fibre-cement boards	According to producer manual	According to producer manual	

Building Element			
<b>Internal substrates</b>			
	<b>Building materials</b>	<b>Type</b>	<b>Dimensions [mm]</b>
A	Gypsum plasterboards	A2-s1,d0 (Type A )	13
	Gypsum plasterboards	A2-s1,d0 (Type A)	13
B	Gypsum plasterboards	A2-s1,d0 (Type DF )	13
	Gypsum plasterboards	A2-s1,d0 (Type DF)	13
C	Gypsum plasterboards	A2-s1,d0 (Type A )	13
	Gypsum plasterboards	A2-s1,d0 (Type A)	13
	Timber based boards (OSB/3 / Plywood)	D-s2,d2	9 / 18
D	Gypsum plasterboards	A2-s1,d0 (Type A )	13
	Gypsum plasterboards	A2-s1,d0 (Type A)	13
	Timber based boards (OSB/3 / Plywood)	D-s2,d2	9 / 18
<b>Fasteners:</b>			
<b>Building material</b>	<b>Type / Dimensions [mm]</b>	<b>Spac. / Dist. [mm]</b>	
		Edge	Middle
Gypsum plasterboards	Screw 3.9x35 / 3.9x50	600 / 200	600 / 300
Timber based boards (OSB/3)	Nail 2.5x50	100	100
Timber based boards (Plywood)	Screw 4.2x55	100	100
	External wall EW-01	Ver 1	01.04.2022
<small>Drawing:</small>			1 : 8
			<small>Scale:</small>
			<small>Page:</small> 2/2

2 External wall (wet-room) – type EW-01-W

Building Element																																																						
<p><b>Wall cross section:</b></p>		<p><b>Building physics characteristics:</b></p> <p>Thermal resistance<sup>1)</sup> (ch. 3.8.1):</p> <table border="1"> <thead> <tr> <th rowspan="2">D<sub>insulation</sub> [mm]</th> <th colspan="2">Mineral glass wool</th> </tr> <tr> <th>U [W/m<sup>2</sup>K]</th> <th>R [m<sup>2</sup>K/W]</th> </tr> </thead> <tbody> <tr> <td>95+95</td> <td>0.21</td> <td>4.74</td> </tr> <tr> <td>95+120</td> <td>0.19</td> <td>5.30</td> </tr> <tr> <td>95+145</td> <td>0.17</td> <td>5.84</td> </tr> <tr> <td>95+170</td> <td>0.16</td> <td>6.39</td> </tr> <tr> <td>95+195</td> <td>0.14</td> <td>6.92</td> </tr> </tbody> </table> <p><small>1) Values given are valid for internal substrates A Values are based on 15% timber proportion in layer 4 and 6</small></p> <p>Vapour permeability and moisture resistance (ch. 3.3.1): no condensation</p> <p>Airborne sound insulation (ch. 3.5.1): R<sub>w</sub> (C; C<sub>v</sub>) ≥ 50 (-2; -7) db</p>			D <sub>insulation</sub> [mm]	Mineral glass wool		U [W/m <sup>2</sup> K]	R [m <sup>2</sup> K/W]	95+95	0.21	4.74	95+120	0.19	5.30	95+145	0.17	5.84	95+170	0.16	6.39	95+195	0.14	6.92																														
D <sub>insulation</sub> [mm]	Mineral glass wool																																																					
	U [W/m <sup>2</sup> K]	R [m <sup>2</sup> K/W]																																																				
95+95	0.21	4.74																																																				
95+120	0.19	5.30																																																				
95+145	0.17	5.84																																																				
95+170	0.16	6.39																																																				
95+195	0.14	6.92																																																				
<p><b>Element composition (from outside to inside):</b></p> <table border="1"> <thead> <tr> <th>Nr</th> <th>Building material</th> <th>Type</th> <th>Dimensions [mm]</th> <th>Spac. / Dist. [mm]</th> </tr> </thead> <tbody> <tr> <td>1</td> <td>External layers (see External layers table)</td> <td></td> <td></td> <td></td> </tr> <tr> <td>2</td> <td>Wind-barrier gypsum plasterboard</td> <td>EH / GM-H; A2-s1,d0</td> <td>≥ 9</td> <td>-</td> </tr> <tr> <td>3</td> <td>Thermal insulation: Mineral glass wool</td> <td>λ<sub>0</sub>=0,035 W/mK; A1</td> <td>95/120/145/170/195</td> <td>-</td> </tr> <tr> <td>4</td> <td>Solid timber frame</td> <td>C24</td> <td>45/95 (120,145,170,195)</td> <td>e ≤ 600</td> </tr> <tr> <td>5</td> <td>Timber based boards</td> <td>OSB/3</td> <td>9</td> <td>-</td> </tr> <tr> <td>6</td> <td>Thermal insulation: Mineral glass wool</td> <td>λ<sub>0</sub>=0,035 W/mK; A1</td> <td>95</td> <td>-</td> </tr> <tr> <td>7</td> <td>Solid timber frame</td> <td>C24</td> <td>45/95</td> <td>e ≤ 600</td> </tr> <tr> <td>6</td> <td>Wet room internal substrates (see Internal substrates in wet room table)</td> <td></td> <td></td> <td></td> </tr> <tr> <td>7</td> <td>Watertight covering kits for wet room</td> <td></td> <td></td> <td></td> </tr> </tbody> </table>					Nr	Building material	Type	Dimensions [mm]	Spac. / Dist. [mm]	1	External layers (see External layers table)				2	Wind-barrier gypsum plasterboard	EH / GM-H; A2-s1,d0	≥ 9	-	3	Thermal insulation: Mineral glass wool	λ <sub>0</sub> =0,035 W/mK; A1	95/120/145/170/195	-	4	Solid timber frame	C24	45/95 (120,145,170,195)	e ≤ 600	5	Timber based boards	OSB/3	9	-	6	Thermal insulation: Mineral glass wool	λ <sub>0</sub> =0,035 W/mK; A1	95	-	7	Solid timber frame	C24	45/95	e ≤ 600	6	Wet room internal substrates (see Internal substrates in wet room table)				7	Watertight covering kits for wet room			
Nr	Building material	Type	Dimensions [mm]	Spac. / Dist. [mm]																																																		
1	External layers (see External layers table)																																																					
2	Wind-barrier gypsum plasterboard	EH / GM-H; A2-s1,d0	≥ 9	-																																																		
3	Thermal insulation: Mineral glass wool	λ <sub>0</sub> =0,035 W/mK; A1	95/120/145/170/195	-																																																		
4	Solid timber frame	C24	45/95 (120,145,170,195)	e ≤ 600																																																		
5	Timber based boards	OSB/3	9	-																																																		
6	Thermal insulation: Mineral glass wool	λ <sub>0</sub> =0,035 W/mK; A1	95	-																																																		
7	Solid timber frame	C24	45/95	e ≤ 600																																																		
6	Wet room internal substrates (see Internal substrates in wet room table)																																																					
7	Watertight covering kits for wet room																																																					
<p><b>Fasteners:</b></p> <table border="1"> <thead> <tr> <th>Nr</th> <th>Building material</th> <th>Type / Dimensions [mm]</th> <th colspan="2">Spac. / Dist. [mm]</th> </tr> </thead> <tbody> <tr> <td>2</td> <td>Wind-barrier gypsum plasterboard</td> <td>According to producer manual</td> <td>Edge</td> <td>Middle</td> </tr> <tr> <td>3/5</td> <td>Solid timber frame</td> <td>Nail 3.1x90</td> <td colspan="2">According to producer manual</td> </tr> <tr> <td>4</td> <td>Timber based boards (OSB/3)</td> <td>Nail 2.5x50</td> <td>≤ 100</td> <td>≤ 100</td> </tr> </tbody> </table>					Nr	Building material	Type / Dimensions [mm]	Spac. / Dist. [mm]		2	Wind-barrier gypsum plasterboard	According to producer manual	Edge	Middle	3/5	Solid timber frame	Nail 3.1x90	According to producer manual		4	Timber based boards (OSB/3)	Nail 2.5x50	≤ 100	≤ 100																														
Nr	Building material	Type / Dimensions [mm]	Spac. / Dist. [mm]																																																			
2	Wind-barrier gypsum plasterboard	According to producer manual	Edge	Middle																																																		
3/5	Solid timber frame	Nail 3.1x90	According to producer manual																																																			
4	Timber based boards (OSB/3)	Nail 2.5x50	≤ 100	≤ 100																																																		
<p><b>External layers</b></p> <table border="1"> <thead> <tr> <th></th> <th>Building materials</th> <th>Type</th> <th>Dimensions [mm]</th> <th>Spac. / Dist.[mm]</th> </tr> </thead> <tbody> <tr> <td rowspan="2">A</td> <td>Vertical timber laths</td> <td>Solid timber</td> <td>30/70</td> <td rowspan="2">e ≤ 600</td> </tr> <tr> <td>Horizontal timber cladding</td> <td>Solid timber</td> <td>≥19</td> </tr> <tr> <td rowspan="3">B</td> <td>Vertical timber laths</td> <td>Solid timber</td> <td>30/70</td> <td>e ≤ 600</td> </tr> <tr> <td>Horizontal timber laths</td> <td>Solid timber</td> <td>30/45</td> <td>e ≤ 600</td> </tr> <tr> <td>Vertical timber cladding</td> <td>Solid timber</td> <td>≥19</td> <td></td> </tr> <tr> <td>C</td> <td>Vertical timber laths</td> <td>Solid timber</td> <td>30/70 (95)</td> <td>e ≤ 600</td> </tr> <tr> <td></td> <td>Fibre-cement boards</td> <td>A2-s1,d0</td> <td>≥8</td> <td></td> </tr> </tbody> </table>						Building materials	Type	Dimensions [mm]	Spac. / Dist.[mm]	A	Vertical timber laths	Solid timber	30/70	e ≤ 600	Horizontal timber cladding	Solid timber	≥19	B	Vertical timber laths	Solid timber	30/70	e ≤ 600	Horizontal timber laths	Solid timber	30/45	e ≤ 600	Vertical timber cladding	Solid timber	≥19		C	Vertical timber laths	Solid timber	30/70 (95)	e ≤ 600		Fibre-cement boards	A2-s1,d0	≥8															
	Building materials	Type	Dimensions [mm]	Spac. / Dist.[mm]																																																		
A	Vertical timber laths	Solid timber	30/70	e ≤ 600																																																		
	Horizontal timber cladding	Solid timber	≥19																																																			
B	Vertical timber laths	Solid timber	30/70	e ≤ 600																																																		
	Horizontal timber laths	Solid timber	30/45	e ≤ 600																																																		
	Vertical timber cladding	Solid timber	≥19																																																			
C	Vertical timber laths	Solid timber	30/70 (95)	e ≤ 600																																																		
	Fibre-cement boards	A2-s1,d0	≥8																																																			
<p><b>Fasteners:</b></p> <table border="1"> <thead> <tr> <th>Building material</th> <th>Type / Dimensions [mm]</th> <th colspan="2">Spac. / Dist. [mm]</th> </tr> </thead> <tbody> <tr> <td>Timber laths</td> <td>Nail 3.1x90 / 3.8x130</td> <td>Edge</td> <td>Middle</td> </tr> <tr> <td>Timber cladding</td> <td>Nail 2.5x50</td> <td colspan="2">2 pcs/joint</td> </tr> <tr> <td>Fibre-cement boards</td> <td>According to producer manual</td> <td colspan="2">min. 1 pcs/joint</td> </tr> <tr> <td></td> <td></td> <td colspan="2">According to producer manual</td> </tr> </tbody> </table>					Building material	Type / Dimensions [mm]	Spac. / Dist. [mm]		Timber laths	Nail 3.1x90 / 3.8x130	Edge	Middle	Timber cladding	Nail 2.5x50	2 pcs/joint		Fibre-cement boards	According to producer manual	min. 1 pcs/joint				According to producer manual																															
Building material	Type / Dimensions [mm]	Spac. / Dist. [mm]																																																				
Timber laths	Nail 3.1x90 / 3.8x130	Edge	Middle																																																			
Timber cladding	Nail 2.5x50	2 pcs/joint																																																				
Fibre-cement boards	According to producer manual	min. 1 pcs/joint																																																				
		According to producer manual																																																				
	External wall (wet-room) EW-01-W	Ver 2	15.08.2023	1 : 8																																																		
<small>Drawing:</small>				1/2																																																		
			<small>Scale:</small>	<small>Page:</small>																																																		

Building Element			
<b>Internal substrates in wet room</b>			
	<b>Building materials</b>	<b>Type</b>	<b>Dimensions [mm]</b>
A	Gypsum plasterboards Gypsum plasterboards	A2-s1,d0 (Type A / DFH2IR) A2-s1,d0 (Type A)	13 13
B	Gypsum plasterboards Gypsum plasterboards	A2-s1,d0 (Type DF / DFH2IR) A2-s1,d0 (Type DF)	13 13
C	Gypsum plasterboards Gypsum plasterboards Timber based boards (OSB/3 / Plywood)	A2-s1,d0 (Type A / DFH2IR) A2-s1,d0 (Type A) D-s2,d2	13 13 9 / 18
D	Gypsum plasterboards Gypsum plasterboards Timber based boards (OSB/3 / Plywood)	A2-s1,d0 (Type A / DFH2IR) A2-s1,d0 (Type A) D-s2,d2	13 13 9 / 18
<b>Fasteners:</b>			
<b>Building material</b>	<b>Type / Dimensions [mm]</b>	<b>Spac. / Dist. [mm]</b>	
		Edge	Middle
Gypsum plasterboards	Screw 3.9x35 / 3.9x50	600 / 200	600 / 300
Timber based boards (OSB/3)	Nail 2.5x50	100	100
Timber based boards (Plywood)	Screw 4.2x55	100	100
		External wall (wet-room) EW-01-W	Ver 1
<small>Drawing:</small>		01.04.2022	1 : 8
		<small>Scale:</small>	<small>Page:</small> 2/2

Building Element																																																																					
<b>Wall cross section:</b> 		<b>Building physics characteristics:</b> Thermal resistance <sup>1)</sup> (Ch. 3.8.1): <table border="1" data-bbox="829 380 1260 548"> <thead> <tr> <th rowspan="2">D<sub>insulation</sub> [mm]</th> <th colspan="2">Mineral glass wool<sup>2)</sup></th> <th colspan="2">Mineral stone wool<sup>3)</sup></th> </tr> <tr> <th>U [W/m<sup>2</sup>K]</th> <th>R [m<sup>2</sup>K/W]</th> <th>U [W/m<sup>2</sup>K]</th> <th>R [m<sup>2</sup>K/W]</th> </tr> </thead> <tbody> <tr> <td>170+45+30</td> <td>0.16</td> <td>6.14</td> <td>0.16</td> <td>6.08</td> </tr> <tr> <td>195+45+30</td> <td>0.15</td> <td>6.67</td> <td>0.15</td> <td>6.61</td> </tr> <tr> <td>220+45+30</td> <td>0.14</td> <td>7.20</td> <td>0.14</td> <td>7.14</td> </tr> </tbody> </table> <p><small>1) Values given are valid for internal substrates A            2) Values are based on 15% timber proportion in layer 4 and 6            3) Values are given for mineral stone wool insulation in layer 3</small></p> Vapour permeability and moisture resistance (Ch. 3.3.1): no condensation  Airborne sound insulation (Ch. 3.5.1): R <sub>w</sub> (C; C <sub>r</sub> ) ≥ 55 ( -4; -11 ) db			D <sub>insulation</sub> [mm]	Mineral glass wool <sup>2)</sup>		Mineral stone wool <sup>3)</sup>		U [W/m <sup>2</sup> K]	R [m <sup>2</sup> K/W]	U [W/m <sup>2</sup> K]	R [m <sup>2</sup> K/W]	170+45+30	0.16	6.14	0.16	6.08	195+45+30	0.15	6.67	0.15	6.61	220+45+30	0.14	7.20	0.14	7.14																																									
D <sub>insulation</sub> [mm]	Mineral glass wool <sup>2)</sup>		Mineral stone wool <sup>3)</sup>																																																																		
	U [W/m <sup>2</sup> K]	R [m <sup>2</sup> K/W]	U [W/m <sup>2</sup> K]	R [m <sup>2</sup> K/W]																																																																	
170+45+30	0.16	6.14	0.16	6.08																																																																	
195+45+30	0.15	6.67	0.15	6.61																																																																	
220+45+30	0.14	7.20	0.14	7.14																																																																	
<b>Element composition (from outside to inside):</b> <table border="1" data-bbox="199 851 1308 1164"> <thead> <tr> <th>Nr</th> <th>Building material</th> <th>Type</th> <th>Dimensions [mm]</th> <th>Spac. / Dist. [mm]</th> </tr> </thead> <tbody> <tr> <td>1</td> <td>External layers (see External layers table)</td> <td></td> <td></td> <td></td> </tr> <tr> <td>2</td> <td>Vapour permeable membrane</td> <td>S<sub>d</sub> ≤ 0.025; E / B-s1,d0</td> <td>≥ 0.15</td> <td>-</td> </tr> <tr> <td>3</td> <td>Wind-barrier board:</td> <td></td> <td></td> <td></td> </tr> <tr> <td></td> <td>- Mineral glass wool</td> <td>λ<sub>D</sub>=0,031 W/mK; A2-s1,d0</td> <td>30</td> <td>-</td> </tr> <tr> <td></td> <td>- Mineral stone wool</td> <td>λ<sub>D</sub>=0,033 W/mK; A1</td> <td>30</td> <td>-</td> </tr> <tr> <td>4</td> <td>Thermal insulation: Mineral glass wool</td> <td>λ<sub>D</sub>=0,035 W/mK; A1</td> <td>45</td> <td>-</td> </tr> <tr> <td></td> <td>Timber battens</td> <td>Solid timber</td> <td>45/45</td> <td>e ≤ 600</td> </tr> <tr> <td>5</td> <td>Timber based boards</td> <td>OSB/3</td> <td>9</td> <td>-</td> </tr> <tr> <td>6</td> <td>Thermal insulation: Mineral glass wool</td> <td>λ<sub>D</sub>=0,035 W/mK; A1</td> <td>170/195/220</td> <td>-</td> </tr> <tr> <td></td> <td>Solid timber frame</td> <td>C24</td> <td>45/170 (195,220)</td> <td>e ≤ 600</td> </tr> <tr> <td>7</td> <td>Vapour barrier (between plasterboards)</td> <td>S<sub>d</sub> ≥ 40; F</td> <td>≥ 0.15</td> <td>-</td> </tr> <tr> <td>8</td> <td>Internal substrates (see Internal substrates table)</td> <td></td> <td></td> <td></td> </tr> </tbody> </table>					Nr	Building material	Type	Dimensions [mm]	Spac. / Dist. [mm]	1	External layers (see External layers table)				2	Vapour permeable membrane	S <sub>d</sub> ≤ 0.025; E / B-s1,d0	≥ 0.15	-	3	Wind-barrier board:					- Mineral glass wool	λ <sub>D</sub> =0,031 W/mK; A2-s1,d0	30	-		- Mineral stone wool	λ <sub>D</sub> =0,033 W/mK; A1	30	-	4	Thermal insulation: Mineral glass wool	λ <sub>D</sub> =0,035 W/mK; A1	45	-		Timber battens	Solid timber	45/45	e ≤ 600	5	Timber based boards	OSB/3	9	-	6	Thermal insulation: Mineral glass wool	λ <sub>D</sub> =0,035 W/mK; A1	170/195/220	-		Solid timber frame	C24	45/170 (195,220)	e ≤ 600	7	Vapour barrier (between plasterboards)	S <sub>d</sub> ≥ 40; F	≥ 0.15	-	8	Internal substrates (see Internal substrates table)			
Nr	Building material	Type	Dimensions [mm]	Spac. / Dist. [mm]																																																																	
1	External layers (see External layers table)																																																																				
2	Vapour permeable membrane	S <sub>d</sub> ≤ 0.025; E / B-s1,d0	≥ 0.15	-																																																																	
3	Wind-barrier board:																																																																				
	- Mineral glass wool	λ <sub>D</sub> =0,031 W/mK; A2-s1,d0	30	-																																																																	
	- Mineral stone wool	λ <sub>D</sub> =0,033 W/mK; A1	30	-																																																																	
4	Thermal insulation: Mineral glass wool	λ <sub>D</sub> =0,035 W/mK; A1	45	-																																																																	
	Timber battens	Solid timber	45/45	e ≤ 600																																																																	
5	Timber based boards	OSB/3	9	-																																																																	
6	Thermal insulation: Mineral glass wool	λ <sub>D</sub> =0,035 W/mK; A1	170/195/220	-																																																																	
	Solid timber frame	C24	45/170 (195,220)	e ≤ 600																																																																	
7	Vapour barrier (between plasterboards)	S <sub>d</sub> ≥ 40; F	≥ 0.15	-																																																																	
8	Internal substrates (see Internal substrates table)																																																																				
<b>Fasteners:</b> <table border="1" data-bbox="199 1187 1308 1344"> <thead> <tr> <th rowspan="2">Nr</th> <th rowspan="2">Building material</th> <th rowspan="2">Type / Dimensions [mm]</th> <th colspan="2">Spac. / Dist. [mm]</th> </tr> <tr> <th>Edge</th> <th>Middle</th> </tr> </thead> <tbody> <tr> <td>3</td> <td>Wind-barrier board</td> <td>According to producer manual</td> <td colspan="2">According to producer manual</td> </tr> <tr> <td>4</td> <td>Timber battens</td> <td>Nail 3.1x90</td> <td colspan="2">min. 2pcs/joint</td> </tr> <tr> <td>5</td> <td>Timber based boards (OSB/3)</td> <td>Nail 2.5x50</td> <td>≤ 100</td> <td>≤ 100</td> </tr> <tr> <td>6</td> <td>Solid timber frame</td> <td>Nail 3.1x90</td> <td colspan="2">min. 2pcs/joint</td> </tr> </tbody> </table>					Nr	Building material	Type / Dimensions [mm]	Spac. / Dist. [mm]		Edge	Middle	3	Wind-barrier board	According to producer manual	According to producer manual		4	Timber battens	Nail 3.1x90	min. 2pcs/joint		5	Timber based boards (OSB/3)	Nail 2.5x50	≤ 100	≤ 100	6	Solid timber frame	Nail 3.1x90	min. 2pcs/joint																																							
Nr	Building material	Type / Dimensions [mm]	Spac. / Dist. [mm]																																																																		
			Edge	Middle																																																																	
3	Wind-barrier board	According to producer manual	According to producer manual																																																																		
4	Timber battens	Nail 3.1x90	min. 2pcs/joint																																																																		
5	Timber based boards (OSB/3)	Nail 2.5x50	≤ 100	≤ 100																																																																	
6	Solid timber frame	Nail 3.1x90	min. 2pcs/joint																																																																		
<b>External layers</b> <table border="1" data-bbox="199 1388 1308 1612"> <thead> <tr> <th></th> <th>Building materials</th> <th>Type</th> <th>Dimensions [mm]</th> <th>Spac. / Dist.[mm]</th> </tr> </thead> <tbody> <tr> <td rowspan="2">A</td> <td>Vertical timber laths</td> <td>Solid timber</td> <td>30/70</td> <td rowspan="2">e ≤ 600</td> </tr> <tr> <td>Horizontal timber cladding</td> <td>Solid timber</td> <td>≥19</td> </tr> <tr> <td rowspan="3">B</td> <td>Vertical timber laths</td> <td>Solid timber</td> <td>30/70</td> <td>e ≤ 600</td> </tr> <tr> <td>Horizontal timber laths</td> <td>Solid timber</td> <td>30/45</td> <td>e ≤ 600</td> </tr> <tr> <td>Vertical timber cladding</td> <td>Solid timber</td> <td>≥19</td> <td></td> </tr> <tr> <td rowspan="2">C</td> <td>Vertical timber laths</td> <td>Solid timber</td> <td>30/70 (95)</td> <td rowspan="2">e ≤ 600</td> </tr> <tr> <td>Fibre-cement boards</td> <td>A2-s1,d0</td> <td>≥8</td> </tr> </tbody> </table>						Building materials	Type	Dimensions [mm]	Spac. / Dist.[mm]	A	Vertical timber laths	Solid timber	30/70	e ≤ 600	Horizontal timber cladding	Solid timber	≥19	B	Vertical timber laths	Solid timber	30/70	e ≤ 600	Horizontal timber laths	Solid timber	30/45	e ≤ 600	Vertical timber cladding	Solid timber	≥19		C	Vertical timber laths	Solid timber	30/70 (95)	e ≤ 600	Fibre-cement boards	A2-s1,d0	≥8																															
	Building materials	Type	Dimensions [mm]	Spac. / Dist.[mm]																																																																	
A	Vertical timber laths	Solid timber	30/70	e ≤ 600																																																																	
	Horizontal timber cladding	Solid timber	≥19																																																																		
B	Vertical timber laths	Solid timber	30/70	e ≤ 600																																																																	
	Horizontal timber laths	Solid timber	30/45	e ≤ 600																																																																	
	Vertical timber cladding	Solid timber	≥19																																																																		
C	Vertical timber laths	Solid timber	30/70 (95)	e ≤ 600																																																																	
	Fibre-cement boards	A2-s1,d0	≥8																																																																		
<b>Fasteners:</b> <table border="1" data-bbox="199 1635 1308 1769"> <thead> <tr> <th rowspan="2">Building material</th> <th rowspan="2">Type / Dimensions [mm]</th> <th colspan="2">Spac. / Dist. [mm]</th> </tr> <tr> <th>Edge</th> <th>Middle</th> </tr> </thead> <tbody> <tr> <td>Timber laths</td> <td>Nail 3.1x90 / 3.8x130</td> <td colspan="2">2 pcs/joint</td> </tr> <tr> <td>Timber cladding</td> <td>Nail 2.5x50</td> <td colspan="2">min. 1 pcs/joint</td> </tr> <tr> <td>Fibre-cement boards</td> <td>According to producer manual</td> <td colspan="2">According to producer manual</td> </tr> </tbody> </table>					Building material	Type / Dimensions [mm]	Spac. / Dist. [mm]		Edge	Middle	Timber laths	Nail 3.1x90 / 3.8x130	2 pcs/joint		Timber cladding	Nail 2.5x50	min. 1 pcs/joint		Fibre-cement boards	According to producer manual	According to producer manual																																																
Building material	Type / Dimensions [mm]	Spac. / Dist. [mm]																																																																			
		Edge	Middle																																																																		
Timber laths	Nail 3.1x90 / 3.8x130	2 pcs/joint																																																																			
Timber cladding	Nail 2.5x50	min. 1 pcs/joint																																																																			
Fibre-cement boards	According to producer manual	According to producer manual																																																																			
		External wall EW-02 <small>Drawing:</small>		Ver 2    15.08.2023    1 : 8    1/2 <small>Scale:    Page:</small>																																																																	


Building Element			
Internal substrates			
	Building materials	Type	Dimensions [mm]
A	Gypsum plasterboards	A2-s1,d0 (Type A )	13
	Gypsum plasterboards	A2-s1,d0 (Type A )	13
B	Gypsum plasterboards	A2-s1,d0 (Type DF )	13
	Gypsum plasterboards	A2-s1,d0 (Type DF )	13
C	Gypsum plasterboards	A2-s1,d0 (Type A )	13
	Gypsum plasterboards	A2-s1,d0 (Type A )	13
	Timber based boards (OSB/3 / Plywood)	D-s2,d2	9 / 18
D	Gypsum plasterboards	A2-s1,d0 (Type A )	13
	Gypsum plasterboards	A2-s1,d0 (Type A )	13
	Timber based boards (OSB/3 / Plywood)	D-s2,d2	9 / 18

**Fasteners:**

Building material	Type / Dimensions [mm]	Spac. / Dist. [mm]	
		Edge	Middle
Gypsum plasterboards	Screw 3.9x35 / 3.9x50	600 / 200	600 / 300
Timber based boards (OSB/3)	Nail 2.5x50	100	100
Timber based boards (Plywood)	Screw 4.2x55	100	100

 <b>KODUMAJA</b>	External wall EW-02	Ver 1	01.04.2022	1 : 8	2/2
---	---------------------	-------	------------	-------	-----



4 External wall (wet-room) – type EW-02-W

**Building Element**

**Wall cross section:**

**Building physics characteristics:**

Thermal resistance<sup>1)</sup> (Ch. 3.3.1):

D <sub>insulation</sub> [mm]	Mineral glass wool <sup>2)</sup>		Mineral stone wool <sup>3)</sup>	
	U [W/m <sup>2</sup> K]	R [m <sup>2</sup> K/W]	U [W/m <sup>2</sup> K]	R [m <sup>2</sup> K/W]
170+45+30	0.16	6.14	0.16	6.08
195+45+30	0.15	6.67	0.15	6.61
220+45+30	0.14	7.20	0.14	7.14

<sup>1)</sup> Values given are valid for internal substrates A  
 Values are based on 15% timber proportion in layer 4 and 6  
<sup>2)</sup> Values are given for mineral glass wool insulation in layer 3  
<sup>3)</sup> Values are given for mineral stone wool insulation in layer 3

Vapour permeability and moisture resistance (Ch. 3.3.1):  
 no condensation

Airborne sound insulation (Ch. 3.5.1):  
 R<sub>w</sub> (C; C<sub>tr</sub>) ≥ 55 ( -4; -11 ) db

**Element composition (from outside to inside):**

Nr	Building material	Type	Dimensions [mm]	Spac. / Dist. [mm]
1	External layers (see External layers table)			
2	Vapour permeable membrane	S <sub>d</sub> ≤ 0.025; E / B-s1,d0	≥ 0.15	-
3	Wind-barrier board: - Mineral glass wool - Mineral stone wool	λ <sub>D</sub> =0,031 W/mK; A2-s1,d0 λ <sub>D</sub> =0,033 W/mK; A1	30 30	- -
4	Thermal insulation: Mineral glass wool Timber battens	λ <sub>D</sub> =0,035 W/mK; A1 Solid timber	45 45/45	- e ≤ 600
5	Timber based boards	OSB/3	9	-
6	Thermal insulation: Mineral glass wool Solid timber frame	λ <sub>D</sub> =0,035 W/mK; A1 C24	170/195/220 45/170 (195,220)	- e ≤ 600
7	Wet room internal substrates (see Internal substrates in wet room table)			
8	Watertight covering kits for wet room			

**Fasteners:**


Nr	Building material	Type / Dimensions [mm]	Spac. / Dist. [mm]
3	Wind-barrier board	According to producer manual	Edge Middle According to producer manual
4	Timber battens	Nail 3.1x90	min. 2pcs/joint
5	Timber based boards (OSB/3)	Nail 2.5x50	≤ 100 ≤ 100
6	Solid timber frame	Nail 3.1x90	min. 2pcs/joint

**External layers**

	Building materials	Type	Dimensions [mm]	Spac. / Dist.[mm]
A	Vertical timber laths	Solid timber	30/70	e ≤ 600
	Horizontal timber cladding	Solid timber	≥19	
B	Vertical timber laths	Solid timber	30/70	e ≤ 600
	Horizontal timber laths	Solid timber	30/45	e ≤ 600
	Vertical timber cladding	Solid timber	≥19	
C	Vertical timber laths	Solid timber	30/70 (95)	e ≤ 600
	Fibre-cement boards	A2-s1,d0	≥8	

**Fasteners:**

Building material	Type / Dimensions [mm]	Spac. / Dist. [mm]
Timber laths	Nail 3.1x90 / 3.8x130	Edge Middle 2 pcs/joint
Timber cladding	Nail 2.5x50	min. 1 pcs/joint
Fibre-cement boards	According to producer manual	According to producer manual

Building Element						
<b>Internal substrates in wet room</b>						
	<b>Building materials</b>	<b>Type</b>	<b>Dimensions [mm]</b>			
A	Gypsum plasterboards	A2-s1,d0 (Type A / DFH2IR)	13			
	Gypsum plasterboards	A2-s1,d0 (Type A)	13			
B	Gypsum plasterboards	A2-s1,d0 (Type DF / DFH2IR)	13			
	Gypsum plasterboards	A2-s1,d0 (Type DF)	13			
C	Gypsum plasterboards	A2-s1,d0 (Type A / DFH2IR)	13			
	Gypsum plasterboards	A2-s1,d0 (Type A)	13			
	Timber based boards (OSB/3 / Plywood)	D-s2,d2	9 / 18			
D	Gypsum plasterboards	A2-s1,d0 (Type A / DFH2IR)	13			
	Gypsum plasterboards	A2-s1,d0 (Type A)	13			
	Timber based boards (OSB/3 / Plywood)	D-s2,d2	9 / 18			
<b>Fasteners:</b>						
<b>Building material</b>	<b>Type / Dimensions [mm]</b>	<b>Spac. / Dist. [mm]</b>				
Gypsum plasterboards	Screw 3.9x35 / 3.9x50	Edge 600 / 200	Middle 600 / 300			
Timber based boards (OSB/3)	Nail 2.5x50	100	100			
Timber based boards (Plywood)	Screw 4.2x55	100	100			
		External wall (wet-room) EW-02-W	Ver 1	01.04.2022	1 : 8	2/2
Drawing:				Scale:		Page:

5 External wall – type EW-03

**Building Element**

**Wall cross section:**

**Building physics characteristics:**

Thermal resistance<sup>1)</sup> (Ch. 3.6.1):

D <sub>insulation</sub> [mm]	Mineral glass wool <sup>2)</sup>		Mineral stone wool <sup>3)</sup>	
	U [W/m <sup>2</sup> K]	R [m <sup>2</sup> K/W]	U [W/m <sup>2</sup> K]	R [m <sup>2</sup> K/W]
170+30	0.20	5.06	0.20	5.00
195+30	0.18	5.58	0.18	5.52
220+30	0.16	6.10	0.17	6.04

<sup>1)</sup> Values given are valid for internal substrates A  
<sup>2)</sup> Values are based on 15% timber proportion in layer 5  
<sup>3)</sup> Values are given for mineral glass wool insulation in layer 3

Vapour permeability and moisture resistance (Ch. 3.3.1):  
 no condensation

Airborne sound insulation (Ch. 3.5.1):  
 Rw (C; C<sub>tr</sub>) ≥ 55 (-4; -11) db

**Element composition (from outside to inside):**

Nr	Building material	Type	Dimensions [mm]	Spac. / Dist. [mm]
1	External layers (see External layers table)			
2	Vapour permeable membrane	$S_d \leq 0.025$ ; E / B-s1,d0	≥ 0.15	-
3	Wind-barrier board: - Mineral glass wool - Mineral stone wool	$\lambda_0=0,031$ W/mK; A2-s1,d0 $\lambda_0=0,033$ W/mK; A1	30 30	- -
4	Timber based boards	OSB/3	9	-
5	Thermal insulation: Mineral glass wool Solid timber frame	$\lambda_0=0,035$ W/mK; A1 C24	170/195/220 45/170 (195,220)	- e ≤ 600
6	Vapour barrier (between plasterboards)	$S_d \geq 40$ ; F	≥ 0.15	-
7	Internal substrates (see Internal substrates layers table)			

**Fasteners:**


Nr	Building material	Type / Dimensions [mm]	Spac. / Dist. [mm]
3	Wind-barrier board	According to producer manual	Edge Middle According to producer manual
4	Timber based boards (OSB/3)	Nail 2.5x50	≤ 100
5	Solid timber frame	Nail 3.1x90	min. 2pcs/joint

**External layers**



	Building materials	Type	Dimensions [mm]	Spac. / Dist. [mm]
A	Vertical timber laths Horizontal timber cladding	Solid timber Solid timber	30/70 ≥19	e ≤ 600
B	Vertical timber laths Horizontal timber laths Vertical timber cladding	Solid timber Solid timber Solid timber	30/70 30/45 ≥19	e ≤ 600 e ≤ 600
C	Vertical timber laths Fibre-cement boards	Solid timber A2-s1,d0	30/70 (95) ≥8	e ≤ 600

**Fasteners:**

Building material	Type / Dimensions [mm]	Spac. / Dist. [mm]
Timber laths	Nail 3.1x90 / 3.8x130	Edge Middle 2 pcs/joint
Timber cladding	Nail 2.5x50	min. 1 pcs/joint
Fibre-cement boards	According to producer manual	According to producer manual

Building Element			
<b>Internal substrates</b>			
	<b>Building materials</b>	<b>Type</b>	<b>Dimensions [mm]</b>
A	Gypsum plasterboards	A2-s1,d0 (Type A )	13
	Gypsum plasterboards	A2-s1,d0 (Type A)	13
B	Gypsum plasterboards	A2-s1,d0 (Type DF )	13
	Gypsum plasterboards	A2-s1,d0 (Type DF)	13
C	Gypsum plasterboards	A2-s1,d0 (Type A )	13
	Gypsum plasterboards	A2-s1,d0 (Type A)	13
	Timber based boards (OSB/3 / Plywood)	D-s2,d2	9 / 18
D	Gypsum plasterboards	A2-s1,d0 (Type A )	13
	Gypsum plasterboards	A2-s1,d0 (Type A)	13
	Timber based boards (OSB/3 / Plywood)	D-s2,d2	9 / 18
<b>Fasteners:</b>			
<b>Building material</b>	<b>Type / Dimensions [mm]</b>	<b>Spac. / Dist. [mm]</b>	
		Edge	Middle
Gypsum plasterboards	Screw 3.9x35 / 3.9x50	600 / 200	600 / 300
Timber based boards (OSB/3)	Nail 2.5x50	100	100
Timber based boards (Plywood)	Screw 4.2x55	100	100
	External wall EW-03	Ver 1	01.04.2022
<small>Drawing:</small>			1 : 8
			<small>Scale:</small>
			<small>Page:</small> 2/2

## 6 External wall (wet-room) – type EW-03-W

Building Element																																												
<b>Wall cross section:</b> 		<b>Building physics characteristics:</b> Thermal resistance <sup>1)</sup> (Ch. 3.8.1): <table border="1" data-bbox="821 369 1244 537"> <thead> <tr> <th rowspan="2">D<sub>insulation</sub> [mm]</th> <th colspan="2">Mineral glass wool<sup>2)</sup></th> <th colspan="2">Mineral stone wool<sup>3)</sup></th> </tr> <tr> <th>U [W/m<sup>2</sup>K]</th> <th>R [m<sup>2</sup>K/W]</th> <th>U [W/m<sup>2</sup>K]</th> <th>R [m<sup>2</sup>K/W]</th> </tr> </thead> <tbody> <tr> <td>170+30</td> <td>0.20</td> <td>5.06</td> <td>0.20</td> <td>5.00</td> </tr> <tr> <td>195+30</td> <td>0.18</td> <td>5.58</td> <td>0.18</td> <td>5.52</td> </tr> <tr> <td>220+30</td> <td>0.16</td> <td>6.10</td> <td>0.17</td> <td>6.04</td> </tr> </tbody> </table> <p><small>1) Values given are valid for internal substrates A            Values are based on 15% timber proportion in layer 5            2) Values are given for mineral glass wool insulation in layer 3            3) Values are given for mineral stone wool insulation in layer 3</small></p> Vapour permeability and moisture resistance (Ch. 3.3.1): no condensation  Airborne sound insulation (Ch. 3.5.1): Rw (C; C <sub>v</sub> ) ≥ 55 ( -4; -11 ) db			D <sub>insulation</sub> [mm]	Mineral glass wool <sup>2)</sup>		Mineral stone wool <sup>3)</sup>		U [W/m <sup>2</sup> K]	R [m <sup>2</sup> K/W]	U [W/m <sup>2</sup> K]	R [m <sup>2</sup> K/W]	170+30	0.20	5.06	0.20	5.00	195+30	0.18	5.58	0.18	5.52	220+30	0.16	6.10	0.17	6.04																
D <sub>insulation</sub> [mm]	Mineral glass wool <sup>2)</sup>		Mineral stone wool <sup>3)</sup>																																									
	U [W/m <sup>2</sup> K]	R [m <sup>2</sup> K/W]	U [W/m <sup>2</sup> K]	R [m <sup>2</sup> K/W]																																								
170+30	0.20	5.06	0.20	5.00																																								
195+30	0.18	5.58	0.18	5.52																																								
220+30	0.16	6.10	0.17	6.04																																								
<b>Element composition (from outside to inside):</b> <table border="1" data-bbox="199 862 1292 1131"> <thead> <tr> <th>Nr</th> <th>Building material</th> <th>Type</th> <th>Dimensions [mm]</th> <th>Spac. / Dist. [mm]</th> </tr> </thead> <tbody> <tr> <td>1</td> <td>External layers (see External layers table)</td> <td></td> <td></td> <td></td> </tr> <tr> <td>2</td> <td>Vapour permeable membrane</td> <td>S<sub>d</sub> ≤ 0.025; E / B-s1,d0</td> <td>≥ 0.15</td> <td>-</td> </tr> <tr> <td>3</td> <td>Wind-barrier board: - Mineral glass wool - Mineral stone wool</td> <td>λ<sub>0</sub>=0,031 W/mK; A2-s1,d0 λ<sub>0</sub>=0,033 W/mK; A1</td> <td>30 30</td> <td>- -</td> </tr> <tr> <td>4</td> <td>Timber based boards</td> <td>OSB/3</td> <td>9</td> <td>-</td> </tr> <tr> <td>5</td> <td>Thermal insulation: Mineral glass wool Solid timber frame</td> <td>λ<sub>0</sub>=0,035 W/mK; A1 C24</td> <td>170/195/220 45/170 (195,220)</td> <td>- e ≤ 600</td> </tr> <tr> <td>6</td> <td>Wet room internal substrates (see Internal substrates in wet room table)</td> <td></td> <td></td> <td></td> </tr> <tr> <td>7</td> <td>Watertight covering kits for wet room</td> <td></td> <td></td> <td></td> </tr> </tbody> </table>					Nr	Building material	Type	Dimensions [mm]	Spac. / Dist. [mm]	1	External layers (see External layers table)				2	Vapour permeable membrane	S <sub>d</sub> ≤ 0.025; E / B-s1,d0	≥ 0.15	-	3	Wind-barrier board: - Mineral glass wool - Mineral stone wool	λ <sub>0</sub> =0,031 W/mK; A2-s1,d0 λ <sub>0</sub> =0,033 W/mK; A1	30 30	- -	4	Timber based boards	OSB/3	9	-	5	Thermal insulation: Mineral glass wool Solid timber frame	λ <sub>0</sub> =0,035 W/mK; A1 C24	170/195/220 45/170 (195,220)	- e ≤ 600	6	Wet room internal substrates (see Internal substrates in wet room table)				7	Watertight covering kits for wet room			
Nr	Building material	Type	Dimensions [mm]	Spac. / Dist. [mm]																																								
1	External layers (see External layers table)																																											
2	Vapour permeable membrane	S <sub>d</sub> ≤ 0.025; E / B-s1,d0	≥ 0.15	-																																								
3	Wind-barrier board: - Mineral glass wool - Mineral stone wool	λ <sub>0</sub> =0,031 W/mK; A2-s1,d0 λ <sub>0</sub> =0,033 W/mK; A1	30 30	- -																																								
4	Timber based boards	OSB/3	9	-																																								
5	Thermal insulation: Mineral glass wool Solid timber frame	λ <sub>0</sub> =0,035 W/mK; A1 C24	170/195/220 45/170 (195,220)	- e ≤ 600																																								
6	Wet room internal substrates (see Internal substrates in wet room table)																																											
7	Watertight covering kits for wet room																																											
<b>Fasteners:</b> <table border="1" data-bbox="199 1176 1292 1310"> <thead> <tr> <th>Nr</th> <th>Building material</th> <th>Type / Dimensions [mm]</th> <th>Spac. / Dist. [mm]</th> </tr> </thead> <tbody> <tr> <td>3</td> <td>Wind-barrier board</td> <td>Accoding to producer manual</td> <td>Edge Middle Accoding to producer manual</td> </tr> <tr> <td>4</td> <td>Timber based boards (OSB/3)</td> <td>Nail 2.5x50</td> <td>≤ 100 ≤ 100</td> </tr> <tr> <td>5</td> <td>Solid timber frame</td> <td>Nail 3.1x90</td> <td>min. 2pcs/joint</td> </tr> </tbody> </table>					Nr	Building material	Type / Dimensions [mm]	Spac. / Dist. [mm]	3	Wind-barrier board	Accoding to producer manual	Edge Middle Accoding to producer manual	4	Timber based boards (OSB/3)	Nail 2.5x50	≤ 100 ≤ 100	5	Solid timber frame	Nail 3.1x90	min. 2pcs/joint																								
Nr	Building material	Type / Dimensions [mm]	Spac. / Dist. [mm]																																									
3	Wind-barrier board	Accoding to producer manual	Edge Middle Accoding to producer manual																																									
4	Timber based boards (OSB/3)	Nail 2.5x50	≤ 100 ≤ 100																																									
5	Solid timber frame	Nail 3.1x90	min. 2pcs/joint																																									
<b>External layers</b> <table border="1" data-bbox="199 1377 1292 1590"> <thead> <tr> <th></th> <th>Building materials</th> <th>Type</th> <th>Dimensions [mm]</th> <th>Spac. / Dist.[mm]</th> </tr> </thead> <tbody> <tr> <td rowspan="2">A</td> <td>Vertical timber laths</td> <td>Solid timber</td> <td>30/70</td> <td rowspan="2">e ≤ 600</td> </tr> <tr> <td>Horizontal timber cladding</td> <td>Solid timber</td> <td>≥19</td> </tr> <tr> <td rowspan="3">B</td> <td>Vertical timber laths</td> <td>Solid timber</td> <td>30/70</td> <td>e ≤ 600</td> </tr> <tr> <td>Horizontal timber laths</td> <td>Solid timber</td> <td>30/45</td> <td>e ≤ 600</td> </tr> <tr> <td>Vertical timber cladding</td> <td>Solid timber</td> <td>≥19</td> <td></td> </tr> <tr> <td rowspan="2">C</td> <td>Vertical timber laths</td> <td>Solid timber</td> <td>30/70 (95)</td> <td rowspan="2">e ≤ 600</td> </tr> <tr> <td>Fibre-cement boards</td> <td>A2-s1,d0</td> <td>≥8</td> </tr> </tbody> </table>						Building materials	Type	Dimensions [mm]	Spac. / Dist.[mm]	A	Vertical timber laths	Solid timber	30/70	e ≤ 600	Horizontal timber cladding	Solid timber	≥19	B	Vertical timber laths	Solid timber	30/70	e ≤ 600	Horizontal timber laths	Solid timber	30/45	e ≤ 600	Vertical timber cladding	Solid timber	≥19		C	Vertical timber laths	Solid timber	30/70 (95)	e ≤ 600	Fibre-cement boards	A2-s1,d0	≥8						
	Building materials	Type	Dimensions [mm]	Spac. / Dist.[mm]																																								
A	Vertical timber laths	Solid timber	30/70	e ≤ 600																																								
	Horizontal timber cladding	Solid timber	≥19																																									
B	Vertical timber laths	Solid timber	30/70	e ≤ 600																																								
	Horizontal timber laths	Solid timber	30/45	e ≤ 600																																								
	Vertical timber cladding	Solid timber	≥19																																									
C	Vertical timber laths	Solid timber	30/70 (95)	e ≤ 600																																								
	Fibre-cement boards	A2-s1,d0	≥8																																									
<b>Fasteners:</b> <table border="1" data-bbox="199 1624 1292 1747"> <thead> <tr> <th>Building material</th> <th>Type / Dimensions [mm]</th> <th>Spac. / Dist. [mm]</th> </tr> </thead> <tbody> <tr> <td>Timber laths</td> <td>Nail 3.1x90 / 3.8x130</td> <td>Edge Middle 2 pcs/joint</td> </tr> <tr> <td>Timber cladding</td> <td>Nail 2.5x50</td> <td>min. 1 pcs/joint</td> </tr> <tr> <td>Fibre-cement boards</td> <td>Accoding to producer manual</td> <td>Accoding to producer manual</td> </tr> </tbody> </table>					Building material	Type / Dimensions [mm]	Spac. / Dist. [mm]	Timber laths	Nail 3.1x90 / 3.8x130	Edge Middle 2 pcs/joint	Timber cladding	Nail 2.5x50	min. 1 pcs/joint	Fibre-cement boards	Accoding to producer manual	Accoding to producer manual																												
Building material	Type / Dimensions [mm]	Spac. / Dist. [mm]																																										
Timber laths	Nail 3.1x90 / 3.8x130	Edge Middle 2 pcs/joint																																										
Timber cladding	Nail 2.5x50	min. 1 pcs/joint																																										
Fibre-cement boards	Accoding to producer manual	Accoding to producer manual																																										
		External wall (wet-room) EW-03-W <small>Drawing:</small>		Ver 2    15.08.2023    1 : 8    1/2 <small>Scale:    Page:</small>																																								

**Building Element**

**Internal substrates in wet room**

	Building materials	Type	Dimensions [mm]
A	Gypsum plasterboards	A2-s1,d0 (Type A / DFH2IR)	13
	Gypsum plasterboards	A2-s1,d0 (Type A)	13
B	Gypsum plasterboards	A2-s1,d0 (Type DF / DFH2IR)	13
	Gypsum plasterboards	A2-s1,d0 (Type DF)	13
C	Gypsum plasterboards	A2-s1,d0 (Type A / DFH2IR)	13
	Gypsum plasterboards	A2-s1,d0 (Type A)	13
	Timber based boards (OSB/3 / Plywood)	D-s2,d2	9 / 18
D	Gypsum plasterboards	A2-s1,d0 (Type A / DFH2IR)	13
	Gypsum plasterboards	A2-s1,d0 (Type A)	13
	Timber based boards (OSB/3 / Plywood)	D-s2,d2	9 / 18

**Fasteners:**

Building material	Type / Dimensions [mm]	Spac. / Dist. [mm]	
		Edge	Middle
Gypsum plasterboards	Screw 3.9x35 / 3.9x50	600 / 200	600 / 300
Timber based boards (OSB/3)	Nail 2.5x50	100	100
Timber based boards (Plywood)	Screw 4.2x55	100	100



External wall (wet-room) EW-03-W

Ver 1

01.04.2022

1 : 8



2/2

Drawing:

Scale:

Page:

7 Internal wall – type IW-01

Building Element						
<b>Wall cross section:</b> 		<b>Building physics characteristics:</b>  Thermal resistance (Ch. 3.6.1): -  Airborne sound insulation (Ch. 3.5.1): Rw ≥ 35 db				
<b>Element composition (from inside to inside):</b>						
Nr	Building material	Type	Dimensions [mm]	Spac. / Dist. [mm]		
1	Internal layers (see Internal layers table)					
2	Thermal insulation: - Mineral glass wool - Mineral stone wool Solid timber frame	A1 A1 Solid timber / finger jointed timber	70/95/120/145 70/95/120/145 45/70 (95/120/145)	- - e ≤ 600		
<b>Fasteners:</b>						
Nr	Building material	Type / Dimensions [mm]	Spac. / Dist. [mm]			
2	Solid timber frame	Nail 3.1x90	Edge	Middle min. 2pcs/joint		
<b>Internal substrates (internal separating walls)</b>						
	Building materials	Type	Dimensions [mm]			
A	Gypsum plasterboards	A2-s1,d0 (Type A)	13			
B	Gypsum plasterboards	A2-s1,d0 (Type A)	13			
	Gypsum plasterboards	A2-s1,d0 (Type A)	13			
C	Gypsum plasterboards	A2-s1,d0 (Type A)	13			
	Timber based boards (OSB/3 / Plywood)	D-s2,d2	9 / 18			
D	Gypsum plasterboards	A2-s1,d0 (Type A)	13			
	Gypsum plasterboards	A2-s1,d0 (Type A)	13			
	Timber based boards (OSB/3 / Plywood)	D-s2,d2	9 / 18			
<b>Fasteners:</b>						
Building material	Type / Dimensions [mm]	Spac. / Dist. [mm]				
Gypsum plasterboards	Screw 3.9x35 / 3.9x50	Edge	Middle			
Timber based boards (OSB/3)	Nail 2.5x50	600 / 200	600 / 300			
Timber based boards (Plywood)	Screw 4.2x55	100	100			
		100	100			
		Internal wall IW-01	Ver 2	15.08.2023	1 : 8	1/1
Drawing:				Scale:	Page:	

8 Internal wall (wet-room) – type IW-01-W

Building Element																																	
<p><b>Wall cross section:</b></p>	<p><b>Building physics characteristics:</b></p> <p>Thermal resistance (Ch. 3.6.1): -</p> <p>Airborne sound insulation (Ch. 3.5.1):                      Rw ≥ 35 db</p>																																
<p><b>Element composition (from inside to inside):</b></p> <table border="1"> <thead> <tr> <th>Nr</th> <th>Building material</th> <th>Type</th> <th>Dimensions [mm]</th> <th>Spac. / Dist. [mm]</th> </tr> </thead> <tbody> <tr> <td>1</td> <td>Internal substrates (see Internal substrates table)</td> <td></td> <td></td> <td></td> </tr> <tr> <td>2</td> <td>Thermal insulation: - Mineral glass wool - Mineral stone wool</td> <td>A1 A1</td> <td>70/95/120/145 70/95/120/145</td> <td>- -</td> </tr> <tr> <td>3</td> <td>Solid timber frame</td> <td>Solid timber / finger jointed timber</td> <td>45/70 (95/120/145)</td> <td>e ≤ 600</td> </tr> <tr> <td>4</td> <td>Wet room internal substrates (see Internal substrates in wet room table)</td> <td></td> <td></td> <td></td> </tr> <tr> <td>4</td> <td>Watertight covering kits for wet room</td> <td></td> <td></td> <td></td> </tr> </tbody> </table>		Nr	Building material	Type	Dimensions [mm]	Spac. / Dist. [mm]	1	Internal substrates (see Internal substrates table)				2	Thermal insulation: - Mineral glass wool - Mineral stone wool	A1 A1	70/95/120/145 70/95/120/145	- -	3	Solid timber frame	Solid timber / finger jointed timber	45/70 (95/120/145)	e ≤ 600	4	Wet room internal substrates (see Internal substrates in wet room table)				4	Watertight covering kits for wet room					
Nr	Building material	Type	Dimensions [mm]	Spac. / Dist. [mm]																													
1	Internal substrates (see Internal substrates table)																																
2	Thermal insulation: - Mineral glass wool - Mineral stone wool	A1 A1	70/95/120/145 70/95/120/145	- -																													
3	Solid timber frame	Solid timber / finger jointed timber	45/70 (95/120/145)	e ≤ 600																													
4	Wet room internal substrates (see Internal substrates in wet room table)																																
4	Watertight covering kits for wet room																																
<p><b>Fasteners:</b></p> <table border="1"> <thead> <tr> <th>Nr</th> <th>Building material</th> <th>Type / Dimensions [mm]</th> <th colspan="2">Spac. / Dist. [mm]</th> </tr> <tr> <td></td> <td></td> <td></td> <th>Edge</th> <th>Middle</th> </tr> </thead> <tbody> <tr> <td>2</td> <td>Solid timber frame</td> <td>Nail 3.1x90</td> <td colspan="2">min. 2pcs/joint</td> </tr> </tbody> </table>		Nr	Building material	Type / Dimensions [mm]	Spac. / Dist. [mm]					Edge	Middle	2	Solid timber frame	Nail 3.1x90	min. 2pcs/joint																		
Nr	Building material	Type / Dimensions [mm]	Spac. / Dist. [mm]																														
			Edge	Middle																													
2	Solid timber frame	Nail 3.1x90	min. 2pcs/joint																														
<p><b>Internal substrates (internal separating walls)</b></p> <table border="1"> <thead> <tr> <th></th> <th>Building materials</th> <th>Type</th> <th>Dimensions [mm]</th> </tr> </thead> <tbody> <tr> <td>A</td> <td>Gypsum plasterboards</td> <td>A2-s1,d0 (Type A)</td> <td>13</td> </tr> <tr> <td rowspan="2">B</td> <td>Gypsum plasterboards</td> <td>A2-s1,d0 (Type A)</td> <td>13</td> </tr> <tr> <td>Gypsum plasterboards</td> <td>A2-s1,d0 (Type A)</td> <td>13</td> </tr> <tr> <td rowspan="2">C</td> <td>Gypsum plasterboards</td> <td>A2-s1,d0 (Type A)</td> <td>13</td> </tr> <tr> <td>Timber based boards (OSB/3 / Plywood)</td> <td>D-s2,d2</td> <td>9 / 18</td> </tr> <tr> <td rowspan="3">D</td> <td>Gypsum plasterboards</td> <td>A2-s1,d0 (Type A)</td> <td>13</td> </tr> <tr> <td>Gypsum plasterboards</td> <td>A2-s1,d0 (Type A)</td> <td>13</td> </tr> <tr> <td>Timber based boards (OSB/3 / Plywood)</td> <td>D-s2,d2</td> <td>9 / 18</td> </tr> </tbody> </table>			Building materials	Type	Dimensions [mm]	A	Gypsum plasterboards	A2-s1,d0 (Type A)	13	B	Gypsum plasterboards	A2-s1,d0 (Type A)	13	Gypsum plasterboards	A2-s1,d0 (Type A)	13	C	Gypsum plasterboards	A2-s1,d0 (Type A)	13	Timber based boards (OSB/3 / Plywood)	D-s2,d2	9 / 18	D	Gypsum plasterboards	A2-s1,d0 (Type A)	13	Gypsum plasterboards	A2-s1,d0 (Type A)	13	Timber based boards (OSB/3 / Plywood)	D-s2,d2	9 / 18
	Building materials	Type	Dimensions [mm]																														
A	Gypsum plasterboards	A2-s1,d0 (Type A)	13																														
B	Gypsum plasterboards	A2-s1,d0 (Type A)	13																														
	Gypsum plasterboards	A2-s1,d0 (Type A)	13																														
C	Gypsum plasterboards	A2-s1,d0 (Type A)	13																														
	Timber based boards (OSB/3 / Plywood)	D-s2,d2	9 / 18																														
D	Gypsum plasterboards	A2-s1,d0 (Type A)	13																														
	Gypsum plasterboards	A2-s1,d0 (Type A)	13																														
	Timber based boards (OSB/3 / Plywood)	D-s2,d2	9 / 18																														
<p><b>Internal substrates in wet room (internal separating walls)</b></p> <table border="1"> <thead> <tr> <th></th> <th>Building materials</th> <th>Type</th> <th>Dimensions [mm]</th> </tr> </thead> <tbody> <tr> <td>A</td> <td>Gypsum plasterboards</td> <td>A2-s1,d0 (Type A / DFH2IR)</td> <td>13</td> </tr> <tr> <td rowspan="2">B</td> <td>Gypsum plasterboards</td> <td>A2-s1,d0 (Type A / DFH2IR)</td> <td>13</td> </tr> <tr> <td>Gypsum plasterboards</td> <td>A2-s1,d0 (Type A)</td> <td>13</td> </tr> <tr> <td rowspan="2">C</td> <td>Gypsum plasterboards</td> <td>A2-s1,d0 (Type A / DFH2IR)</td> <td>13</td> </tr> <tr> <td>Timber based boards (OSB/3 / Plywood)</td> <td>D-s2,d2</td> <td>9 / 18</td> </tr> <tr> <td rowspan="3">D</td> <td>Gypsum plasterboards</td> <td>A2-s1,d0 (Type A / DFH2IR)</td> <td>13</td> </tr> <tr> <td>Gypsum plasterboards</td> <td>A2-s1,d0 (Type A)</td> <td>13</td> </tr> <tr> <td>Timber based boards (OSB/3 / Plywood)</td> <td>D-s2,d2</td> <td>9 / 18</td> </tr> </tbody> </table>			Building materials	Type	Dimensions [mm]	A	Gypsum plasterboards	A2-s1,d0 (Type A / DFH2IR)	13	B	Gypsum plasterboards	A2-s1,d0 (Type A / DFH2IR)	13	Gypsum plasterboards	A2-s1,d0 (Type A)	13	C	Gypsum plasterboards	A2-s1,d0 (Type A / DFH2IR)	13	Timber based boards (OSB/3 / Plywood)	D-s2,d2	9 / 18	D	Gypsum plasterboards	A2-s1,d0 (Type A / DFH2IR)	13	Gypsum plasterboards	A2-s1,d0 (Type A)	13	Timber based boards (OSB/3 / Plywood)	D-s2,d2	9 / 18
	Building materials	Type	Dimensions [mm]																														
A	Gypsum plasterboards	A2-s1,d0 (Type A / DFH2IR)	13																														
B	Gypsum plasterboards	A2-s1,d0 (Type A / DFH2IR)	13																														
	Gypsum plasterboards	A2-s1,d0 (Type A)	13																														
C	Gypsum plasterboards	A2-s1,d0 (Type A / DFH2IR)	13																														
	Timber based boards (OSB/3 / Plywood)	D-s2,d2	9 / 18																														
D	Gypsum plasterboards	A2-s1,d0 (Type A / DFH2IR)	13																														
	Gypsum plasterboards	A2-s1,d0 (Type A)	13																														
	Timber based boards (OSB/3 / Plywood)	D-s2,d2	9 / 18																														
<p><b>Fasteners:</b></p> <table border="1"> <thead> <tr> <th>Building material</th> <th>Type / Dimensions [mm]</th> <th colspan="2">Spac. / Dist. [mm]</th> </tr> <tr> <td></td> <td></td> <th>Edge</th> <th>Middle</th> </tr> </thead> <tbody> <tr> <td>Gypsum plasterboards</td> <td>Screw 3.9x35 / 3.9x50</td> <td>600 / 200</td> <td>600 / 300</td> </tr> <tr> <td>Timber based boards (OSB/3)</td> <td>Nail 2.5x50</td> <td>100</td> <td>100</td> </tr> <tr> <td>Timber based boards (Plywood)</td> <td>Screw 4.2x55</td> <td>100</td> <td>100</td> </tr> </tbody> </table>		Building material	Type / Dimensions [mm]	Spac. / Dist. [mm]				Edge	Middle	Gypsum plasterboards	Screw 3.9x35 / 3.9x50	600 / 200	600 / 300	Timber based boards (OSB/3)	Nail 2.5x50	100	100	Timber based boards (Plywood)	Screw 4.2x55	100	100												
Building material	Type / Dimensions [mm]	Spac. / Dist. [mm]																															
		Edge	Middle																														
Gypsum plasterboards	Screw 3.9x35 / 3.9x50	600 / 200	600 / 300																														
Timber based boards (OSB/3)	Nail 2.5x50	100	100																														
Timber based boards (Plywood)	Screw 4.2x55	100	100																														
	Internal wall (wet-room) IW-01-W <small>Drawing</small>	Ver 2	15.08.2023	1 : 8	1/1																												
				Scale:	Page:																												




9 Load bearing separating wall – type PW-01

Building Element																																																												
<p><b>Wall cross section:</b></p>			<p><b>Building physics characteristics:</b></p> <p>Thermal resistance (Ch. 3.6.1): -</p> <p>Airborne sound insulation (Ch. 3.5.1):</p> <p><math>R'_w \geq 60</math> db</p> <p><math>R'_w + C_{50-3150} \geq 52</math> db</p> <p><math>R'_w + C_{50-5000} \geq 52</math> db</p>																																																									
<p><b>Element composition (from inside to inside):</b></p> <table border="1"> <thead> <tr> <th>Nr</th> <th>Building material</th> <th>Type</th> <th>Dimensions [mm]</th> <th>Spac. / Dist. [mm]</th> </tr> </thead> <tbody> <tr> <td>1</td> <td>Internal layers (see Internal layers table)</td> <td></td> <td></td> <td></td> </tr> <tr> <td>2</td> <td>Thermal insulation: Mineral glass wool</td> <td>A1</td> <td>95</td> <td>-</td> </tr> <tr> <td>3</td> <td>Solid timber frame</td> <td>C24</td> <td>45/95</td> <td><math>e \leq 600</math></td> </tr> <tr> <td>3</td> <td>Timber based boards</td> <td>OSB/3</td> <td>9</td> <td>-</td> </tr> <tr> <td>4</td> <td>Air gap</td> <td>-</td> <td>~32</td> <td>-</td> </tr> </tbody> </table>					Nr	Building material	Type	Dimensions [mm]	Spac. / Dist. [mm]	1	Internal layers (see Internal layers table)				2	Thermal insulation: Mineral glass wool	A1	95	-	3	Solid timber frame	C24	45/95	$e \leq 600$	3	Timber based boards	OSB/3	9	-	4	Air gap	-	~32	-																										
Nr	Building material	Type	Dimensions [mm]	Spac. / Dist. [mm]																																																								
1	Internal layers (see Internal layers table)																																																											
2	Thermal insulation: Mineral glass wool	A1	95	-																																																								
3	Solid timber frame	C24	45/95	$e \leq 600$																																																								
3	Timber based boards	OSB/3	9	-																																																								
4	Air gap	-	~32	-																																																								
<p><b>Fasteners:</b></p> <table border="1"> <thead> <tr> <th rowspan="2">Nr</th> <th rowspan="2">Building material</th> <th rowspan="2">Type / Dimensions [mm]</th> <th colspan="2">Spac. / Dist. [mm]</th> </tr> <tr> <th>Edge</th> <th>Middle</th> </tr> </thead> <tbody> <tr> <td>2</td> <td>Solid timber frame</td> <td>Nail 3.1x90</td> <td>2pcs/joint</td> <td>-</td> </tr> <tr> <td>3</td> <td>Timber based boards (OSB/3)</td> <td>Nail 2.5x50</td> <td><math>\leq 100</math></td> <td><math>\leq 100</math></td> </tr> </tbody> </table>					Nr	Building material	Type / Dimensions [mm]	Spac. / Dist. [mm]		Edge	Middle	2	Solid timber frame	Nail 3.1x90	2pcs/joint	-	3	Timber based boards (OSB/3)	Nail 2.5x50	$\leq 100$	$\leq 100$																																							
Nr	Building material	Type / Dimensions [mm]	Spac. / Dist. [mm]																																																									
			Edge	Middle																																																								
2	Solid timber frame	Nail 3.1x90	2pcs/joint	-																																																								
3	Timber based boards (OSB/3)	Nail 2.5x50	$\leq 100$	$\leq 100$																																																								
<p><b>Internal substrates</b></p> <table border="1"> <thead> <tr> <th></th> <th>Building materials</th> <th>Type</th> <th>Dimensions [mm]</th> </tr> </thead> <tbody> <tr> <td rowspan="2">A</td> <td>Gypsum plasterboards</td> <td>A2-s1,d0 (Type A)</td> <td>13</td> </tr> <tr> <td>Gypsum plasterboards</td> <td>A2-s1,d0 (Type A)</td> <td>13</td> </tr> <tr> <td rowspan="2">B</td> <td>Gypsum plasterboards</td> <td>A2-s1,d0 (Type DF)</td> <td>13</td> </tr> <tr> <td>Gypsum plasterboards</td> <td>A2-s1,d0 (Type DF)</td> <td>13</td> </tr> <tr> <td rowspan="3">C</td> <td>Gypsum plasterboards</td> <td>A2-s1,d0 (Type A)</td> <td>13</td> </tr> <tr> <td>Gypsum plasterboards</td> <td>A2-s1,d0 (Type A)</td> <td>13</td> </tr> <tr> <td>Timber based boards (OSB/3 / Plywood)</td> <td>D-s2,d2</td> <td>9 / 18</td> </tr> <tr> <td rowspan="3">D</td> <td>Gypsum plasterboards</td> <td>A2-s1,d0 (Type A)</td> <td>13</td> </tr> <tr> <td>Gypsum plasterboards</td> <td>A2-s1,d0 (Type A)</td> <td>13</td> </tr> <tr> <td>Timber based boards (OSB/3 / Plywood)</td> <td>D-s2,d2</td> <td>9 / 18</td> </tr> </tbody> </table> <p><b>Fasteners:</b></p> <table border="1"> <thead> <tr> <th rowspan="2">Building material</th> <th rowspan="2">Type / Dimensions [mm]</th> <th colspan="2">Spac. / Dist. [mm]</th> </tr> <tr> <th>Edge</th> <th>Middle</th> </tr> </thead> <tbody> <tr> <td>Gypsum plasterboards</td> <td>Screw 3.9x35 / 3.9x50</td> <td>600 / 200</td> <td>600 / 300</td> </tr> <tr> <td>Timber based boards (OSB/3)</td> <td>Nail 2.5x50</td> <td>100</td> <td>100</td> </tr> <tr> <td>Timber based boards (Plywood)</td> <td>Screw 4.2x55</td> <td>100</td> <td>100</td> </tr> </tbody> </table>						Building materials	Type	Dimensions [mm]	A	Gypsum plasterboards	A2-s1,d0 (Type A)	13	Gypsum plasterboards	A2-s1,d0 (Type A)	13	B	Gypsum plasterboards	A2-s1,d0 (Type DF)	13	Gypsum plasterboards	A2-s1,d0 (Type DF)	13	C	Gypsum plasterboards	A2-s1,d0 (Type A)	13	Gypsum plasterboards	A2-s1,d0 (Type A)	13	Timber based boards (OSB/3 / Plywood)	D-s2,d2	9 / 18	D	Gypsum plasterboards	A2-s1,d0 (Type A)	13	Gypsum plasterboards	A2-s1,d0 (Type A)	13	Timber based boards (OSB/3 / Plywood)	D-s2,d2	9 / 18	Building material	Type / Dimensions [mm]	Spac. / Dist. [mm]		Edge	Middle	Gypsum plasterboards	Screw 3.9x35 / 3.9x50	600 / 200	600 / 300	Timber based boards (OSB/3)	Nail 2.5x50	100	100	Timber based boards (Plywood)	Screw 4.2x55	100	100
	Building materials	Type	Dimensions [mm]																																																									
A	Gypsum plasterboards	A2-s1,d0 (Type A)	13																																																									
	Gypsum plasterboards	A2-s1,d0 (Type A)	13																																																									
B	Gypsum plasterboards	A2-s1,d0 (Type DF)	13																																																									
	Gypsum plasterboards	A2-s1,d0 (Type DF)	13																																																									
C	Gypsum plasterboards	A2-s1,d0 (Type A)	13																																																									
	Gypsum plasterboards	A2-s1,d0 (Type A)	13																																																									
	Timber based boards (OSB/3 / Plywood)	D-s2,d2	9 / 18																																																									
D	Gypsum plasterboards	A2-s1,d0 (Type A)	13																																																									
	Gypsum plasterboards	A2-s1,d0 (Type A)	13																																																									
	Timber based boards (OSB/3 / Plywood)	D-s2,d2	9 / 18																																																									
Building material	Type / Dimensions [mm]	Spac. / Dist. [mm]																																																										
		Edge	Middle																																																									
Gypsum plasterboards	Screw 3.9x35 / 3.9x50	600 / 200	600 / 300																																																									
Timber based boards (OSB/3)	Nail 2.5x50	100	100																																																									
Timber based boards (Plywood)	Screw 4.2x55	100	100																																																									
		Load bearing separating wall PW-01 <small>Drawing:</small>	Ver 2	15.08.2023	1 : 8 <small>Scale:</small>	1/1 <small>Page:</small>																																																						

10 Load bearing separating wall (wet-room) – type PW-01-W

Building Element

Wall cross section:



Building physics characteristics:

Thermal resistance (Ch. 3.8.1): -

Airborne sound insulation (Ch. 3.5.1):

$R'_w \geq 60 \text{ db}$   
 $R'_w + C_{50-3150} \geq 52 \text{ db}$   
 $R'_w + C_{50-5000} \geq 52 \text{ db}$

Element composition (from inside to inside):

Nr	Building material	Type	Dimensions [mm]	Spac. / Dist. [mm]
1	Watertight covering kits for wet room			
2	Wet room internal substrates (see Internal substrates in wet room table)			
3	Thermal insulation: Mineral glass wool Solid timber frame	A1 C24	95 45/95	- e ≤ 600
4	Timber based boards	OSB/3	9	-
5	Air gap	-	~32	-

Fasteners:

Nr	Building material	Type / Dimensions [mm]	Spac. / Dist. [mm]	
			Edge	Middle
2	Solid timber frame	Nail 3.1x90	2pcs/joint	
3	Timber based boards (OSB/3)	Nail 2.5x50	≤ 100	≤ 100

Internal substrates in wet room

	Building materials	Type	Dimensions [mm]
A	Gypsum plasterboards	A2-s1,d0 (Type A / DFH2IR)	13
	Gypsum plasterboards	A2-s1,d0 (Type A)	13
B	Gypsum plasterboards	A2-s1,d0 (Type DF / DFH2IR)	13
	Gypsum plasterboards	A2-s1,d0 (Type DF)	13
C	Gypsum plasterboards	A2-s1,d0 (Type A / DFH2IR)	13
	Gypsum plasterboards	A2-s1,d0 (Type A)	13
	Timber based boards (OSB/3 / Plywood)	D-s2,d2	9 / 18
D	Gypsum plasterboards	A2-s1,d0 (Type A / DFH2IR)	13
	Gypsum plasterboards	A2-s1,d0 (Type A)	13
	Timber based boards (OSB/3 / Plywood)	D-s2,d2	9 / 18

Fasteners:

Building material	Type / Dimensions [mm]	Spac. / Dist. [mm]	
		Edge	Middle
Gypsum plasterboards	Screw 3.9x35 / 3.9x50	600 / 200	600 / 300
Timber based boards (OSB/3)	Nail 2.5x50	100	100
Timber based boards (Plywood)	Screw 4.2x55	100	100



Load bearing separating wall (wet-room) PW-01-W

Ver 2

15.08.2023

1 : 8

1/1

11 Intermediate storey partition floor – type CE-01

Building Element																																																																					
<p><b>Floor cross section:</b></p>		<p><b>Building physics characteristics:</b></p> <p>Thermal resistance (Ch. 3.6.1): -</p> <p>Airborne sound insulation (Ch. 3.5.1):  <math>R'_w \geq 60</math> db  <math>R'_{w,C50-3150} \geq 56</math> db  <math>R'_{w,C50-5000} \geq 56</math> db  <math>D_{nT,w} \geq 60</math> db  <math>D_{nT,w,C50-3150} \geq 56</math> db</p> <p>Impact sound insulation (Ch. 3.5.2):  <math>L'_{n,w} \leq 50</math> db  <math>L'_{n,w,C1,50-2500} \leq 53</math> db  <math>L'_{nT,w} \leq 50</math> db  <math>L'_{nT,w,C1,50-2500} \leq 53</math> db</p>																																																																			
<p><b>Element composition (from top downwards):</b></p> <table border="1"> <thead> <tr> <th>Nr</th> <th>Building material</th> <th>Type</th> <th>Dimensions [mm]</th> <th>Spac. / Dist. [mm]</th> </tr> </thead> <tbody> <tr> <td>1</td> <td>Floor layers</td> <td></td> <td></td> <td>-</td> </tr> <tr> <td>2</td> <td>Timber based boards (Chipboard)</td> <td>P6</td> <td>22/28</td> <td>-</td> </tr> <tr> <td>3</td> <td>Thermal insulation: Mineral glass wool</td> <td><math>\lambda_0=0,035</math> W/mK; A1</td> <td>195/220/245/250/300</td> <td>-</td> </tr> <tr> <td></td> <td>Solid timber frame / or I-joint frame</td> <td>C24 C30+</td> <td>45/195 (220/245) 47 (70)/250 (300)</td> <td><math>e \leq 600</math> <math>e \leq 600</math></td> </tr> <tr> <td>4</td> <td>Steel net</td> <td>galvanized</td> <td>1</td> <td>-</td> </tr> <tr> <td>5</td> <td>Air gap</td> <td>-</td> <td><math>\geq 59</math></td> <td>-</td> </tr> <tr> <td>6</td> <td>Module protection film</td> <td>Water resistance = W1; E</td> <td><math>\geq 0.2</math></td> <td>-</td> </tr> <tr> <td>7</td> <td>Timber based boards (Chipboard)</td> <td>P2</td> <td>12</td> <td>-</td> </tr> <tr> <td>8</td> <td>Thermal insulation: Mineral glass wool</td> <td><math>\lambda_0=0,035</math> W/mK; A1</td> <td>95/120/145</td> <td>-</td> </tr> <tr> <td></td> <td>Solid timber frame</td> <td>C24</td> <td>45/95 (120/145)</td> <td><math>e \leq 600</math></td> </tr> <tr> <td>9</td> <td>Timber laths</td> <td>Solid timber</td> <td><math>\geq 21/60</math></td> <td><math>e \leq 400</math></td> </tr> <tr> <td>10</td> <td>Ceiling plasterboards (see ceiling layers table)</td> <td></td> <td></td> <td>-</td> </tr> </tbody> </table>					Nr	Building material	Type	Dimensions [mm]	Spac. / Dist. [mm]	1	Floor layers			-	2	Timber based boards (Chipboard)	P6	22/28	-	3	Thermal insulation: Mineral glass wool	$\lambda_0=0,035$ W/mK; A1	195/220/245/250/300	-		Solid timber frame / or I-joint frame	C24 C30+	45/195 (220/245) 47 (70)/250 (300)	$e \leq 600$ $e \leq 600$	4	Steel net	galvanized	1	-	5	Air gap	-	$\geq 59$	-	6	Module protection film	Water resistance = W1; E	$\geq 0.2$	-	7	Timber based boards (Chipboard)	P2	12	-	8	Thermal insulation: Mineral glass wool	$\lambda_0=0,035$ W/mK; A1	95/120/145	-		Solid timber frame	C24	45/95 (120/145)	$e \leq 600$	9	Timber laths	Solid timber	$\geq 21/60$	$e \leq 400$	10	Ceiling plasterboards (see ceiling layers table)			-
Nr	Building material	Type	Dimensions [mm]	Spac. / Dist. [mm]																																																																	
1	Floor layers			-																																																																	
2	Timber based boards (Chipboard)	P6	22/28	-																																																																	
3	Thermal insulation: Mineral glass wool	$\lambda_0=0,035$ W/mK; A1	195/220/245/250/300	-																																																																	
	Solid timber frame / or I-joint frame	C24 C30+	45/195 (220/245) 47 (70)/250 (300)	$e \leq 600$ $e \leq 600$																																																																	
4	Steel net	galvanized	1	-																																																																	
5	Air gap	-	$\geq 59$	-																																																																	
6	Module protection film	Water resistance = W1; E	$\geq 0.2$	-																																																																	
7	Timber based boards (Chipboard)	P2	12	-																																																																	
8	Thermal insulation: Mineral glass wool	$\lambda_0=0,035$ W/mK; A1	95/120/145	-																																																																	
	Solid timber frame	C24	45/95 (120/145)	$e \leq 600$																																																																	
9	Timber laths	Solid timber	$\geq 21/60$	$e \leq 400$																																																																	
10	Ceiling plasterboards (see ceiling layers table)			-																																																																	
<p><b>Fasteners:</b></p> <table border="1"> <thead> <tr> <th rowspan="2">Nr</th> <th rowspan="2">Building material</th> <th rowspan="2">Type / Dimensions [mm]</th> <th colspan="2">Spac. / Dist. [mm]</th> </tr> <tr> <th>Edge</th> <th>Middle</th> </tr> </thead> <tbody> <tr> <td>2</td> <td>Chipboard</td> <td>Nail 2.6x65 + Glue</td> <td>150</td> <td>200</td> </tr> <tr> <td>3/8</td> <td>Solid timber frame</td> <td>Nail 3.1x90</td> <td colspan="2">min. 2pcs/joint</td> </tr> <tr> <td>3</td> <td>I-joint frame</td> <td>Nail 3.1x90 / 3.8x130</td> <td colspan="2">min. 4+2pcs/joint</td> </tr> <tr> <td>7</td> <td>Chipboard</td> <td>Nail 2.5x50</td> <td>200</td> <td>300</td> </tr> <tr> <td>9</td> <td>Timber laths</td> <td>Nail 2.8x65</td> <td colspan="2">min. 2pcs/joint</td> </tr> </tbody> </table>					Nr	Building material	Type / Dimensions [mm]	Spac. / Dist. [mm]		Edge	Middle	2	Chipboard	Nail 2.6x65 + Glue	150	200	3/8	Solid timber frame	Nail 3.1x90	min. 2pcs/joint		3	I-joint frame	Nail 3.1x90 / 3.8x130	min. 4+2pcs/joint		7	Chipboard	Nail 2.5x50	200	300	9	Timber laths	Nail 2.8x65	min. 2pcs/joint																																		
Nr	Building material	Type / Dimensions [mm]	Spac. / Dist. [mm]																																																																		
			Edge	Middle																																																																	
2	Chipboard	Nail 2.6x65 + Glue	150	200																																																																	
3/8	Solid timber frame	Nail 3.1x90	min. 2pcs/joint																																																																		
3	I-joint frame	Nail 3.1x90 / 3.8x130	min. 4+2pcs/joint																																																																		
7	Chipboard	Nail 2.5x50	200	300																																																																	
9	Timber laths	Nail 2.8x65	min. 2pcs/joint																																																																		
<p><b>Ceiling layers</b></p> <table border="1"> <thead> <tr> <th></th> <th>Building materials</th> <th>Type</th> <th>Dimensions [mm]</th> </tr> </thead> <tbody> <tr> <td rowspan="2">A</td> <td>Gypsum plasterboards</td> <td>A2-s1,d0 (Type A)</td> <td>13</td> </tr> <tr> <td>Gypsum plasterboards</td> <td>A2-s1,d0 (Type A)</td> <td>13</td> </tr> <tr> <td rowspan="2">B</td> <td>Gypsum plasterboards</td> <td>A2-s1,d0 (Type DF)</td> <td>15</td> </tr> <tr> <td>Gypsum plasterboards</td> <td>A2-s1,d0 (Type DF)</td> <td>15</td> </tr> </tbody> </table>						Building materials	Type	Dimensions [mm]	A	Gypsum plasterboards	A2-s1,d0 (Type A)	13	Gypsum plasterboards	A2-s1,d0 (Type A)	13	B	Gypsum plasterboards	A2-s1,d0 (Type DF)	15	Gypsum plasterboards	A2-s1,d0 (Type DF)	15																																															
	Building materials	Type	Dimensions [mm]																																																																		
A	Gypsum plasterboards	A2-s1,d0 (Type A)	13																																																																		
	Gypsum plasterboards	A2-s1,d0 (Type A)	13																																																																		
B	Gypsum plasterboards	A2-s1,d0 (Type DF)	15																																																																		
	Gypsum plasterboards	A2-s1,d0 (Type DF)	15																																																																		
<p><b>Fasteners:</b></p> <table border="1"> <thead> <tr> <th rowspan="2">Building material</th> <th rowspan="2">Type / Dimensions [mm]</th> <th colspan="2">Spac. / Dist. [mm]</th> </tr> <tr> <th>Edge</th> <th>Middle</th> </tr> </thead> <tbody> <tr> <td>Gypsum plasterboards</td> <td>Screw 3.9x35 / 3.9x50</td> <td>200</td> <td>300</td> </tr> </tbody> </table>					Building material	Type / Dimensions [mm]	Spac. / Dist. [mm]		Edge	Middle	Gypsum plasterboards	Screw 3.9x35 / 3.9x50	200	300																																																							
Building material	Type / Dimensions [mm]	Spac. / Dist. [mm]																																																																			
		Edge	Middle																																																																		
Gypsum plasterboards	Screw 3.9x35 / 3.9x50	200	300																																																																		
	Intermediate storey partition floor CE-01	Ver 2	15.08.2023	1 : 8 Page: 1/2																																																																	

**Building Element**

Floor layers 1/2		
	Building materials	Dimensions [mm]
A	Parquet	8-14
	Flooring underlay	2
B	Parquet	8-14
	Flooring underlay	2
	Sound absorbing layer	7
C	Parquet	8-14
	Flooring underlay	2
	Floor gypsum plasterboard	13
	Floor gypsum plasterboard	13
D	Parquet	8-14
	Flooring underlay	2
	Sound-absorbant layer	7
	Floor gypsum plasterboard	13
	Floor gypsum plasterboard	13
E	Parquet	8-14
	Flooring underlay	2
	Floor gypsum plasterboard	13
	Floor gypsum plasterboard	13
	Sound damping board	20

Floor layers 2/2		
	Building materials	Dimensions [mm]
F	Parquet	8-14
	Flooring underlay	2
	Sound-absorbant layer	7
	Reinforced concrete	≥38
G	PVC	3
	Self-leveling compound	4
H	PVC	3
	Self-leveling compound	4
	Floor gypsum plasterboard	13
	Floor gypsum plasterboard	13
I	PVC	3
	Self-leveling compound	4
	Floor gypsum plasterboard	13
	Floor gypsum plasterboard	13
	Sound-absorbant layer	7



Intermediate storey partition floor CE-01

Ver 1

01.04.2022

1 : 8

2/2

Drawing:

Scale:

Page:


12 Intermediate storey partition floor (wet room)– type CE-02

Building Element																																																																									
<p><b>Floor cross section:</b></p>		<p><b>Building physics characteristics:</b></p> <p>Thermal resistance (Ch. 3.6.1): -</p> <p>Airborne sound insulation (Ch. 3.5.1): -</p> <p>Impact sound insulation (Ch. 3.5.2): -</p>																																																																							
<p><b>Element composition (from top downwards):</b></p> <table border="1"> <thead> <tr> <th>Nr</th> <th>Building material</th> <th>Type</th> <th>Dimensions [mm]</th> <th>Spac. / Dist. [mm]</th> </tr> </thead> <tbody> <tr> <td>1</td> <td>Watertight covering kits for wet room</td> <td></td> <td></td> <td></td> </tr> <tr> <td>2</td> <td>Reinforced concrete</td> <td>≥C25; B500</td> <td>≥35 ; 5x150x150</td> <td>-</td> </tr> <tr> <td>3</td> <td>Steel sheet</td> <td>zinc steel</td> <td>1</td> <td>-</td> </tr> <tr> <td>4</td> <td>Thermal insulation: Mineral glass wool</td> <td><math>\lambda_0=0,035</math> W/mK; A1</td> <td>250</td> <td>-</td> </tr> <tr> <td></td> <td>I-joist frame</td> <td>C30+</td> <td>47 (70)/ 250</td> <td>e ≤ 400</td> </tr> <tr> <td>5</td> <td>Steel net</td> <td>galvanized</td> <td>1</td> <td>-</td> </tr> <tr> <td>6</td> <td>Air gap</td> <td>-</td> <td>≥59</td> <td>-</td> </tr> <tr> <td>7</td> <td>Module protection film</td> <td>Water resistance = W1; E</td> <td>≥0.2</td> <td>-</td> </tr> <tr> <td>8</td> <td>Timber based boards (Chipboard)</td> <td>P2</td> <td>12</td> <td>-</td> </tr> <tr> <td>9</td> <td>Thermal insulation: Mineral glass wool</td> <td><math>\lambda_0=0,035</math> W/mK; A1</td> <td>95/120/145</td> <td>-</td> </tr> <tr> <td></td> <td>Solid timber frame</td> <td>C24</td> <td>45/95 (120/145)</td> <td>e ≤ 600</td> </tr> <tr> <td>10</td> <td>Timber laths</td> <td>Solid timber</td> <td>≥21/60</td> <td>e ≤ 400</td> </tr> <tr> <td>11</td> <td>Ceiling layers (see ceiling layers table)</td> <td></td> <td></td> <td></td> </tr> </tbody> </table>				Nr	Building material	Type	Dimensions [mm]	Spac. / Dist. [mm]	1	Watertight covering kits for wet room				2	Reinforced concrete	≥C25; B500	≥35 ; 5x150x150	-	3	Steel sheet	zinc steel	1	-	4	Thermal insulation: Mineral glass wool	$\lambda_0=0,035$ W/mK; A1	250	-		I-joist frame	C30+	47 (70)/ 250	e ≤ 400	5	Steel net	galvanized	1	-	6	Air gap	-	≥59	-	7	Module protection film	Water resistance = W1; E	≥0.2	-	8	Timber based boards (Chipboard)	P2	12	-	9	Thermal insulation: Mineral glass wool	$\lambda_0=0,035$ W/mK; A1	95/120/145	-		Solid timber frame	C24	45/95 (120/145)	e ≤ 600	10	Timber laths	Solid timber	≥21/60	e ≤ 400	11	Ceiling layers (see ceiling layers table)			
Nr	Building material	Type	Dimensions [mm]	Spac. / Dist. [mm]																																																																					
1	Watertight covering kits for wet room																																																																								
2	Reinforced concrete	≥C25; B500	≥35 ; 5x150x150	-																																																																					
3	Steel sheet	zinc steel	1	-																																																																					
4	Thermal insulation: Mineral glass wool	$\lambda_0=0,035$ W/mK; A1	250	-																																																																					
	I-joist frame	C30+	47 (70)/ 250	e ≤ 400																																																																					
5	Steel net	galvanized	1	-																																																																					
6	Air gap	-	≥59	-																																																																					
7	Module protection film	Water resistance = W1; E	≥0.2	-																																																																					
8	Timber based boards (Chipboard)	P2	12	-																																																																					
9	Thermal insulation: Mineral glass wool	$\lambda_0=0,035$ W/mK; A1	95/120/145	-																																																																					
	Solid timber frame	C24	45/95 (120/145)	e ≤ 600																																																																					
10	Timber laths	Solid timber	≥21/60	e ≤ 400																																																																					
11	Ceiling layers (see ceiling layers table)																																																																								
<p><b>Fasteners:</b></p> <table border="1"> <thead> <tr> <th rowspan="2">Nr</th> <th rowspan="2">Building material</th> <th rowspan="2">Type / Dimensions [mm]</th> <th colspan="2">Spac. / Dist. [mm]</th> </tr> <tr> <th>Edge</th> <th>Middle</th> </tr> </thead> <tbody> <tr> <td>3</td> <td>Steel sheet</td> <td>Nail 2,5x25</td> <td>600</td> <td>600</td> </tr> <tr> <td>4</td> <td>I-joist frame</td> <td>Nail 3.1x90 / 3.8x130</td> <td colspan="2">min. 4+2pcs/joint</td> </tr> <tr> <td>8</td> <td>Chipboard</td> <td>Nail 2.5x50</td> <td>200</td> <td>300</td> </tr> <tr> <td>9</td> <td>Solid timber frame</td> <td>Nail 3.1x90</td> <td colspan="2">min. 2pcs/joint</td> </tr> <tr> <td>10</td> <td>Timber laths</td> <td>Nail 2.8x65</td> <td colspan="2">min. 2pcs/joint</td> </tr> </tbody> </table>				Nr	Building material	Type / Dimensions [mm]	Spac. / Dist. [mm]		Edge	Middle	3	Steel sheet	Nail 2,5x25	600	600	4	I-joist frame	Nail 3.1x90 / 3.8x130	min. 4+2pcs/joint		8	Chipboard	Nail 2.5x50	200	300	9	Solid timber frame	Nail 3.1x90	min. 2pcs/joint		10	Timber laths	Nail 2.8x65	min. 2pcs/joint																																							
Nr	Building material	Type / Dimensions [mm]	Spac. / Dist. [mm]																																																																						
			Edge	Middle																																																																					
3	Steel sheet	Nail 2,5x25	600	600																																																																					
4	I-joist frame	Nail 3.1x90 / 3.8x130	min. 4+2pcs/joint																																																																						
8	Chipboard	Nail 2.5x50	200	300																																																																					
9	Solid timber frame	Nail 3.1x90	min. 2pcs/joint																																																																						
10	Timber laths	Nail 2.8x65	min. 2pcs/joint																																																																						
<p><b>Ceiling layers</b></p> <table border="1"> <thead> <tr> <th></th> <th>Building materials</th> <th>Type</th> <th>Dimensions [mm]</th> </tr> </thead> <tbody> <tr> <td rowspan="2">A</td> <td>Gypsum plasterboards</td> <td>A2-s1,d0 (Type A)</td> <td>13</td> </tr> <tr> <td>Gypsum plasterboards</td> <td>A2-s1,d0 (Type A)</td> <td>13</td> </tr> <tr> <td rowspan="2">B</td> <td>Gypsum plasterboards</td> <td>A2-s1,d0 (Type DF)</td> <td>15</td> </tr> <tr> <td>Gypsum plasterboards</td> <td>A2-s1,d0 (Type DF)</td> <td>15</td> </tr> </tbody> </table>					Building materials	Type	Dimensions [mm]	A	Gypsum plasterboards	A2-s1,d0 (Type A)	13	Gypsum plasterboards	A2-s1,d0 (Type A)	13	B	Gypsum plasterboards	A2-s1,d0 (Type DF)	15	Gypsum plasterboards	A2-s1,d0 (Type DF)	15																																																				
	Building materials	Type	Dimensions [mm]																																																																						
A	Gypsum plasterboards	A2-s1,d0 (Type A)	13																																																																						
	Gypsum plasterboards	A2-s1,d0 (Type A)	13																																																																						
B	Gypsum plasterboards	A2-s1,d0 (Type DF)	15																																																																						
	Gypsum plasterboards	A2-s1,d0 (Type DF)	15																																																																						
<p><b>Fasteners:</b></p> <table border="1"> <thead> <tr> <th rowspan="2">Building material</th> <th rowspan="2">Type / Dimensions [mm]</th> <th colspan="2">Spac. / Dist. [mm]</th> </tr> <tr> <th>Edge</th> <th>Middle</th> </tr> </thead> <tbody> <tr> <td>Gypsum plasterboards</td> <td>Screw 3.9x35 / 3.9x50</td> <td>200</td> <td>300</td> </tr> </tbody> </table>				Building material	Type / Dimensions [mm]	Spac. / Dist. [mm]		Edge	Middle	Gypsum plasterboards	Screw 3.9x35 / 3.9x50	200	300																																																												
Building material	Type / Dimensions [mm]	Spac. / Dist. [mm]																																																																							
		Edge	Middle																																																																						
Gypsum plasterboards	Screw 3.9x35 / 3.9x50	200	300																																																																						
		Intermediate storey partition floor (wet-room) CE-02	Ver 2	15.08.2023	1 : 8	1/1																																																																			
Drawing:					Scale:	Page:																																																																			

13 Floor – type FE-01

Building Element

Floor section:



Building physics characteristics:

Thermal resistance<sup>1)</sup> (Ch. 3.6.1):

Insulation [mm]	Mineral glass wool	
	U [W/m <sup>2</sup> K]	R [m <sup>2</sup> K/W]
245	0.18	5.65
245+45	0.15	6.57
250	0.16	6.33
300	0.13	7.52
350	0.12	8.71
400	0.10	9.90
450	0.09	11.09
500	0.08	12.28

<sup>1)</sup> Values given are valid without floor layers  
Values are based on 7.5 / 15% timber proportion in layer 3 and 20% timber proportion in layer 4

Vapour permeability and moisture resistance (Ch. 3.3.1):  
no condensation

Element composition (from top downwards):

Nr	Building material	Type	Dimensions [mm]	Spac. / Dist. [mm]
1	Floor layers			-
2	Timber based boards (Chipboard)	P6	22/28	-
3	Thermal insulation: Mineral glass wool	$\lambda_D=0,035$ W/mK; A1	245/290/300/350/400/450/500	-
	Solid timber frame / or I-joist frame	C24	45/245 (290)	$e \leq 600$
		C30+	47 (70)/250 (300/350/400/450/500)	$e \leq 600$
4	Timber laths	Solid timber	$\geq 21/60$	$e \leq 400$
5	Wind-barrier gypsum plasterboard	EH / GM-H; A2-s1,d0	$\geq 9$	-
6	Timber batten	Impregnated solid timber	20/45	$e \leq 400$

Fasteners:

Nr	Building material	Type / Dimensions [mm]	Spac. / Dist. [mm]	
			Edge	Middle
2	Chipboard	Nail 2.8x65 + Glue	150	200
3	Solid timber frame	Nail 3.8x130	min. 2pcs/joint	
3	I-joist frame	Nail 3.1x90 / 3.8x130	min. 4+2pcs/joint	
4	Timber laths	Nail 2.8x65	min. 2pcs/joint	
5	Wind-barrier gypsum plasterboard	According to producer manual	According to producer manual	
6	Timber batten	Nail 2.5x50	min. 1pcs/joint	

Floor layers 1/2		
	Building materials	Dimensions [mm]
A	Parquet	8-14
	Flooring underlay	2
B	Parquet	8-14
	Flooring underlay	2
	Sound absorbing layer	7
C	Parquet	8-14
	Flooring underlay	2
	Floor gypsum plasterboard	13
	Floor gypsum plasterboard	13
D	Parquet	8-14
	Flooring underlay	2
	Sound-absorbant layer	7
	Floor gypsum plasterboard	13
E	Parquet	8-14
	Flooring underlay	2
	Floor gypsum plasterboard	13
	Floor gypsum plasterboard	13
	Sound damping board	20

Floor layers 2/2		
	Building materials	Dimensions [mm]
F	Parquet	8-14
	Flooring underlay	2
	Sound-absorbant layer	7
	Reinforced concrete	$\geq 38$
G	PVC	3
	Self-leveling compound	4
H	PVC	3
	Self-leveling compound	4
	Floor gypsum plasterboard	13
	Floor gypsum plasterboard	13
I	PVC	3
	Self-leveling compound	4
	Floor gypsum plasterboard	13
	Floor gypsum plasterboard	13
	Sound-absorbant layer	7



Floor FE-01

Drawing:

Ver 2

15.08.2023

1 : 8

1/1

Scale:

Page:

Building Element																																	
<b>Floor section:</b>		<b>Building physics characteristics:</b>																															
		<b>Thermal resistance<sup>1)</sup> (Ch. 3.8.1):</b> <table border="1"> <thead> <tr> <th rowspan="2">D<sub>insulation</sub> [mm]</th> <th colspan="2">Mineral glass wool</th> </tr> <tr> <th>U [W/m<sup>2</sup>K]</th> <th>R [m<sup>2</sup>K/W]</th> </tr> </thead> <tbody> <tr><td>245+13</td><td>0.17</td><td>5.90</td></tr> <tr><td>245+45+13</td><td>0.15</td><td>6.81</td></tr> <tr><td>250+13</td><td>0.15</td><td>6.58</td></tr> <tr><td>300+13</td><td>0.13</td><td>7.78</td></tr> <tr><td>350+13</td><td>0.11</td><td>8.97</td></tr> <tr><td>400+13</td><td>0.10</td><td>10.16</td></tr> <tr><td>450+13</td><td>0.09</td><td>11.35</td></tr> <tr><td>500+13</td><td>0.08</td><td>12.54</td></tr> </tbody> </table>			D <sub>insulation</sub> [mm]	Mineral glass wool		U [W/m <sup>2</sup> K]	R [m <sup>2</sup> K/W]	245+13	0.17	5.90	245+45+13	0.15	6.81	250+13	0.15	6.58	300+13	0.13	7.78	350+13	0.11	8.97	400+13	0.10	10.16	450+13	0.09	11.35	500+13	0.08	12.54
		D <sub>insulation</sub> [mm]	Mineral glass wool																														
U [W/m <sup>2</sup> K]	R [m <sup>2</sup> K/W]																																
245+13	0.17	5.90																															
245+45+13	0.15	6.81																															
250+13	0.15	6.58																															
300+13	0.13	7.78																															
350+13	0.11	8.97																															
400+13	0.10	10.16																															
450+13	0.09	11.35																															
500+13	0.08	12.54																															
		<sup>1)</sup> Values given are valid without floor layers Values are based on 7.5 / 15% timber proportion in layer 3  <b>Vapour permeability and moisture resistance (Ch. 3.3.1):</b> no condensation																															
<b>Element composition (from top downwards):</b>																																	
Nr	Building material	Type	Dimensions [mm]	Spac. / Dist. [mm]																													
1	Floor layers			-																													
2	Timber based boards (Chipboard)	P6	22/28	-																													
3	Thermal insulation: Mineral glass wool	$\lambda_D=0,035$ W/mK; A1	245/290/300/350/400/450/500	-																													
	Solid timber frame / or I-joist frame	C24 C30+	45/245 (290)	e ≤ 600																													
4	Wind-barrier board: Mineral glass wool	$\lambda_D=0,031$ W/mK; A2-s1,d0	47 (70)/250 (300/350/400/450/500)	e ≤ 600																													
5	Vapour permeable membrane	$S_d \leq 0,025$ ; E	13	-																													
6	Timber laths	Impregnated solid timber	≥ 0.15 20/45	- e ≤ 400																													
<b>Fasteners:</b>																																	
Nr	Building material	Type / Dimensions [mm]	Spac. / Dist. [mm]																														
2	Chipboard	Nail 2.8x65 + Glue	Edge 150	Middle 200																													
3	Solid timber frame	Nail 3.8x130	min. 2pcs/joint																														
3	I-joist frame	Nail 3.1x90 / 3.8x130	min. 4+2pcs/joint																														
4	Wind-barrier board	Staples 10.7x32	≤ 600, min. 1pcs																														
6	Timber laths	Nail min. 2.5x50	min. 1pcs/joint																														
<b>Floor layers 1/2</b>		<b>Floor layers 2/2</b>																															
	Building materials	Dimensions [mm]																															
A	Parquet Flooring underlay	8-14 2																															
B	Parquet Flooring underlay Sound absorbing layer	8-14 2 7																															
C	Parquet Flooring underlay Floor gypsum plasterboard Floor gypsum plasterboard	8-14 2 13 13																															
D	Parquet Flooring underlay Sound-absorbant layer Floor gypsum plasterboard Floor gypsum plasterboard	8-14 2 7 13 13																															
E	Parquet Flooring underlay Floor gypsum plasterboard Floor gypsum plasterboard Sound damping board	8-14 2 13 13 20																															
F	Parquet Flooring underlay Sound-absorbant layer Reinforced concrete	8-14 2 7 ≥38																															
G	PVC Self-leveling compound	3 4																															
H	PVC Self-leveling compound Floor gypsum plasterboard Floor gypsum plasterboard	3 4 13 13																															
I	PVC Self-leveling compound Floor gypsum plasterboard Floor gypsum plasterboard Sound-absorbant layer	3 4 13 13 7																															
		Floor FE-02	Ver 2	15.08.2023	1 : 8	1/1																											
Drawing:					Scale:	Page:																											


5 Floor (wet-room) type FE-03

Building Element																								
<b>Floor cross section:</b> 		<b>Building physics characteristics:</b> Thermal resistance <sup>1)</sup> (Ch. 3.6.1): <table border="1"> <thead> <tr> <th rowspan="2">D<sub>insulation</sub> [mm]</th> <th colspan="2">Mineral glass wool</th> </tr> <tr> <th>U [W/m<sup>2</sup>K]</th> <th>R [m<sup>2</sup>K/W]</th> </tr> </thead> <tbody> <tr> <td>250</td> <td>0.17</td> <td>6.01</td> </tr> <tr> <td>300</td> <td>0.14</td> <td>7.20</td> </tr> <tr> <td>350</td> <td>0.12</td> <td>8.39</td> </tr> <tr> <td>400</td> <td>0.10</td> <td>9.58</td> </tr> <tr> <td>450</td> <td>0.09</td> <td>10.77</td> </tr> </tbody> </table> <p><sup>1)</sup> Values given are valid without floor layers                      Values are based on 7.5 / 15% timber proportion in layer 4</p> Vapour permeability and moisture resistance (Ch. 3.3.1): no condensation			D <sub>insulation</sub> [mm]	Mineral glass wool		U [W/m <sup>2</sup> K]	R [m <sup>2</sup> K/W]	250	0.17	6.01	300	0.14	7.20	350	0.12	8.39	400	0.10	9.58	450	0.09	10.77
D <sub>insulation</sub> [mm]	Mineral glass wool																							
	U [W/m <sup>2</sup> K]	R [m <sup>2</sup> K/W]																						
250	0.17	6.01																						
300	0.14	7.20																						
350	0.12	8.39																						
400	0.10	9.58																						
450	0.09	10.77																						
<b>Element composition (from top downwards):</b>																								
Nr	Building material	Type	Dimensions [mm]	Spac. / Dist. [mm]																				
1	Watertight covering kits for wet room			-																				
2	Reinforced concrete	≥C25; B500	≥35 ; 5x150x150	-																				
3	Steel sheet	zinc steel	1	-																				
4	Thermal insulation: Mineral glass wool	λ <sub>0</sub> =0,035 W/mK; A1	250/300/350/400/450	e ≤ 400																				
	I-joist frame	C30+	47 (70) 250 (300/350/400/450)	e ≤ 400																				
5	Wind-barrier gypsum plasterboard	EH / GM-H; A2-s1,d0	≥ 9	-																				
6	Timber batten	Impregnated solid timber	20/45	e ≤ 400																				
<b>Fasteners:</b>																								
Nr	Building material	Type / Dimensions [mm]	Spac. / Dist. [mm]																					
3	Steel sheet	Nail 2,5x25	Edge	Middle																				
4	I-joist frame	Nail 3.1x90 / 3.8x130	600	600																				
5	Wind-barrier gypsum plasterboard	According to producer manual	min. 4+2pcs/joint																					
6	Timber batten	Nail 2.5x50	According to producer manual min. 1 pcs/joint																					
		Floor (wet-room) FE-03	Ver 2	15.08.2023	1 : 8	1/1																		



**Building Element**

**Floor cross section:**



**Building physics characteristics:**

Thermal resistance<sup>1)</sup> (Ch. 3.8.1):

D <sub>insulation</sub> [mm]	Mineral glass wool	
	U [W/m <sup>2</sup> K]	R [m <sup>2</sup> K/W]
250+13	0.16	6.43
300+13	0.13	7.62
350+13	0.11	8.81
400+13	0.10	10.00
450+13	0.09	11.19

<sup>1)</sup> Values given are valid without floor layers  
Values are based on 7.5 / 15% timber proportion in layer 4

Vapour permeability and moisture resistance (Ch. 3.3.1):  
no condensation

**Element composition (from top downwards):**

Nr	Building material	Type	Dimensions [mm]	Spac. / Dist. [mm]
1	Watertight covering kits for wet room			
2	Reinforced concrete	≥C25; B500	≥35 ; 5x150x150	-
3	Steel sheet	zinc steel	1	-
4	Thermal insulation: Mineral glass wool	λ <sub>0</sub> =0,035 W/mK; A1	250 (300/350/400/450)	e ≤ 400
	I-joint frame	C30+	47 (70)/250 (300/350/400/450)	e ≤ 400
5	Wind-barrier board: Mineral glass wool	λ <sub>0</sub> =0,031 W/mK; A2-s1,d0	13	-
6	Vapour permeable membrane	S <sub>d</sub> ≤ 0.025; E	≥ 0.15	-
7	Timber laths	Impregnated solid timber	20/45	e ≤ 400


**Fasteners:**

Nr	Building material	Type / Dimensions [mm]	Spac. / Dist. [mm]	
			Edge	Middle
3	Steel sheet	Nail 2,5x25	600	600
4	I-joint frame	Nail 3.1x90 / 3.8x130	min. 4+2pcs/joint	
5	Wind-barrier board	Staples 10.7x32	≤ 600, min. 1pcs	
7	Timber laths	Nail min. 2.5x50	min. 1pcs/joint	

17 Roof (sloped) RE-01

Building Element

Roof (sloped) cross section:



Building physics characteristics:

Thermal resistance<sup>1)</sup> (ch. 3.8.1):

D <sub>insulation</sub> [mm]	Mineral glass wool	
	U [W/m <sup>2</sup> K]	R [m <sup>2</sup> K/W]
300	0.13	7.51
350	0.12	8.70
400	0.10	9.89
450	0.09	11.08
500	0.08	12.27

<sup>1)</sup> Values given are valid for ceiling layers A  
Values are based on 7.5 / 15 % timber proportion in layer 6 and 20% timber proportion in layer 7

Vapour permeability and moisture resistance (ch. 3.3.1):  
no condensation

Element composition (from top downwards):

Nr	Building material	Type	Dimensions [mm]	Spac. / Dist. [mm]
1	Roof cover (SBS / PVC)	B <sub>roof</sub>	≥ 1.6	-
2	Timber based boards (Chipboard)	P5	18	-
3	Timber laths	C24	45/ 45 (70/95/120)	e ≤ 400
4	Vapour permeable membrane	S <sub>d</sub> ≤ 0.025; E	≥ 0.15	-
5	Timber based boards	OSB/3	9	-
6	Thermal insulation: Mineral glass wool	λ <sub>D</sub> =0,035 W/mK; A1	(300/350/400/450/500)	-
7	Timber I-joint frame	C30+	47 (70)/300 (350/ 400/ 450/ 500)	e ≤ 600
8	Timber battens	Solid timber	≥21/60	e ≤ 400
9	Vapour barrier (between plasterboards)	S <sub>d</sub> ≥ 40; F	≥ 0.15	-
9	Ceiling layers (see ceiling layers table)			

Fasteners:

Nr	Building material	Type / Dimensions [mm]	Spac. / Dist. [mm]	
			Edge	Middle
2	Chipboard	Nail 2.5x60	150	200
3	Timber laths	Screw 6.0x120	Project specific	
6	Timber based boards (OSB/3)	Nail 2.5x50	≤ 200	≤ 300
7	I-joint frame	Nail 3.1x90/ 3.8x130	min. 4+2pcs/ joint	
8	Timber battens	Nail 2.8x65	2pcs/ joint	

Ceiling layers

	Building materials	Type	Dimensions [mm]
A	Gypsum plasterboards	A2-s1,d0 (Type A)	13
	Gypsum plasterboards	A2-s1,d0 (Type A)	13
B	Gypsum plasterboards	A2-s1,d0 (Type DF)	15
	Gypsum plasterboards	A2-s1,d0 (Type DF)	15

Fasteners:

Building material	Type / Dimensions [mm]	Spac. / Dist. [mm]	
		Edge	Middle
Gypsum plasterboards	Screw 3.9x35 / 3.9x50	200	300

**Building Element**

**Roof (flat) cross section:**

**Building physics characteristics:**

Thermal resistance<sup>1)</sup> (ch. 3.6.1):

D <sub>insulation</sub> [mm]	Mineral glass wool	
	U [W/m <sup>2</sup> K]	R [m <sup>2</sup> K/W]
300	0.13	7.51
350	0.12	8.70
400	0.10	9.89
450	0.09	11.08
500	0.08	12.27

<sup>1)</sup> Values given are valid for ceiling layers A  
 Values are based on 7.5 / 15 % timber proportion in layer 6 and 20% timber proportion in layer 7

Vapour permeability and moisture resistance (ch. 3.3.1):  
 no condensation

**Element composition (from top downwards):**

Nr	Building material	Type	Dimensions [mm]	Spac. / Dist. [mm]
1	Roof cover (SBS / PVC)	B <sub>roof</sub>	≥ 1.6	-
2	Timber based boards (Chipboard)	P5	18	-
3	Timber frame sloped /	C24	45/ min. 70 (height according to slope)	e ≤ 400
4	Timber cross-laths	Solid timber	45/70	e ≤ 600
5	Vapour permeable membrane	S <sub>d</sub> ≤ 0.025; E	≥ 0.15	-
6	Timber based boards	OSB/3	9	-
7	Thermal insulation: Mineral glass wool	λ <sub>D</sub> =0,035 W/mK; A1	(300/350/400/450/500)	-
	Timber I-joist frame	C30+	47 (70)/300 (350/ 400/ 450/ 500)	e ≤ 600
8	Timber battens	Solid timber	≥21/60	e ≤ 400
9	Vapour barrier (between plasterboards)	S <sub>d</sub> ≥ 40; F	≥ 0.15	-
10	Ceiling layers (see ceiling layers table)			-

**Fasteners:**

Nr	Building material	Type / Dimensions [mm]	Spac. / Dist. [mm]	
			Edge	Middle
2	Chipboard	Nail 2.5x60	150	200
3	Timber frame sloped	Nail 5.0x90		
5	Timber laths	Screw 6.0x120	1pcs/ joint	
6	Timber based boards (OSB/3)	Nail 2.5x50	≤ 200	≤ 300
7	I-joist frame	Nail 3.1x90/ 3.8x130	min. 4+2pcs/ joint	
8	Timber battens	Nail 2.8x65	2pcs/ joint	

**Ceiling layers**

	Building materials	Type	Dimensions [mm]
A	Gypsum plasterboards	A2-s1,d0 (Type A)	13
	Gypsum plasterboards	A2-s1,d0 (Type A)	13
B	Gypsum plasterboards	A2-s1,d0 (Type DF)	15
	Gypsum plasterboards	A2-s1,d0 (Type DF)	15

**Fasteners:**

Building material	Type / Dimensions [mm]	Spac. / Dist. [mm]	
		Edge	Middle
Gypsum plasterboards	Screw 3.9x35 / 3.9x50	200	300

## Annex A2 – Material and component specifications

Table A2-1 – Material and component specifications "Kodumaja Building modules"

MATERIAL GROUP	PRODUCT	STANDARD	MAIN DIMENSIONS (mm)	CHARACTERISTICS				
				MECHANICAL	BUILDING PHYSICS			REACTION TO FIRE
					$\rho$ (kg/m <sup>3</sup> )	$\lambda$ (W/mK)	$\mu$ (-)	
<b>Structural Timber</b>								
	Strength graded timber, Spruce, C24	EN 14081-1	≥22	420	0.12	50	1600	D-s2,d0 (2003/593/EC)
	Glued laminated timber, Spruce, GL28h	EN 14080	≥22	≥450	0.12	40	1600	D-s2,d0 (2005/610/EC)
	Structural laminated veneer lumber, Spruce,	EN 14374	≥18	≥400	0.12	-	-	D-s2,d0 ((EU) 2017/2293)
	Light composite wood-based beams	ETA based on EAD 130367-00-0304 <sup>1)</sup> Light Composite Wood-based Beams and Columns	Various	-	0.13	-	-	D-s2,d0 (ETA)
<b>Non-structural Timber</b>								
	Solid timber	Kodumaja factory production control (FPC) defined criteria	Various	≥450	0.12	40	-	-
	Finger jointed timber	-	Various	-	0.12	-	-	-
<b>Internal Panelling and Cladding</b>								
Wood based boards	Oriented strand board, OSB 3	EN 13986	9	≥600	0.13	50	1700	D-s2,d0 (2007/348/EC)
	Particleboard, P2	EN 13986	12	≥600	0.13	50	1700	D-s2,d0, Dfl-s1 (2007/348/EC)
	Particleboard, P5	EN 13986	18	≥600	0.13	50	1700	D-s2,d0, Dfl-s1 (2007/348/EC)
	Particleboard, P6	EN 13986	22, 28	≥600	0.13	50	1700	D-s2,d0, Dfl-s1 (2007/348/EC)
	Plywood	EN 13986	18	≥450	0.13	200	1600	D-s2,d0 (2007/348/EC)
Gypsum boards	Gypsum plasterboard type A	EN 520	12.5	≥600	0.21-0.25	10	1000	A2-s1,d0 (2006/673/EC)
	Gypsum plasterboard type DF	EN 520	12.5 / 15	≥800	0.25	10	1000	A2-s1,d0 (2006/673/EC)
	Gypsum plasterboard type DFH2IR	EN 520	12.5 / 15	≥800	0.25	10	1000	A2-s1,d0 (2006/673/EC)
	Gypsum plasterboard EH2	EN 520	9.5	≥600	0.25	10-15	1000	A2-s1,d0 (2006/673/EC)
	Gypsum plasterboard DIR	EN 520	12.5	≥1000	0.25	10	1000	A2-s1,d0 (2006/673/EC)
	Gypsum fibre boards type GM-H1	EN 15283-1	9.5	≥600	0.25	10	1000	A2-s1,d0 (EN 15283-2)
<b>External Panelling and Cladding</b>								
	Wood cladding	EN 14915	≥19	450	0.13	50	1600	D-s2,d0 (2006/213/EC)
	Fibre-cement boards	EN 12467	≥8	-	-	-	-	A2-s1,d0 (EN 12467)
<b>Thermal insulation</b>								
	Mineral glass wool	EN 13162	50-200	≥15	0.035	1	-	A1 (EN 13162)
	Mineral glass wool	EN 13162	30	-	0.031	1	-	A2-s1,d0 (EN 13162)
	Mineral stone wool	EN 13162	50-200	≥28	0.037	1	-	A1 (EN 13162)
	Mineral stone wool	EN 13162	30	-	0.033	1	-	A1 (EN 13162)
	Extruded polystyrene XPS	EN 13164	20-30	-	-	-	-	E (EN 13164)
<b>Membranes</b>								
	Vapour barrier	EN 13984	≥0.15	-	-	$S_d \geq 40$ m	-	NPD
	Vapour permeable membrane	EN 13859-2	-	-	-	$S_d \leq 0.2$ m	-	B-s1,d0
	Watertight covering kits for wet room floors and/or walls	ETA based on EAD 030352-00-0503 <sup>1) 2)</sup> Watertight covering kits for wet room	-	-	-	$S_d \geq 10$ m	-	-

MATERIAL GROUP	PRODUCT	STANDARD	MAIN DIMENSIONS (mm)	CHARACTERISTICS			
				MECHANICAL $\rho$ (kg/m <sup>3</sup> )	BUILDING PHYSICS		REACTION TO FIRE Euroclass (EN 13501-1)
					$\lambda$ (W/mK)	$\mu$ (-)	
		floors and/or walls					
<b>Sealing Materials</b>							
	Fire resistance acrylic sealant	-	-	-	-	-	-
	Elastic assembly adhesive	-	-	-	-	-	Technical data sheet
	Neutral silicone sealant	EN 15651	-	-	-	-	-
	Acrylic sealant	EN 15651	-	-	-	-	-
	Airtight sealing tape	-	-	-	-	-	Technical data sheet
	Door / Window interior tape	-	-	-	-	-	Technical data sheet
	Door / Window exterior tape	-	-	-	-	-	Technical data sheet
	Screed material and floor screeds	EN 13813	-	-	-	-	-
<b>Fasteners</b>							
	Screws / nails / staples for interior and exterior applications	EN 14592, ETA based on EAD 130186-00-0603 <sup>1)</sup>	Various	-	-	-	A1 (96/603/EC)
	Screws for the fixing of gypsum plasterboard	EN 14566	Various	-	-	-	A1 (96/603/EC)
	Joist hangers	ETA based on EAD 130186-00-0603 <sup>1)</sup> Three-Dimensional Nailing Plates	Various	-	-	-	A1 (96/603/EC)
	Angle brackets	ETA based on EAD 130186-00-0603 <sup>1)</sup> Three-Dimensional Nailing Plates	Various	-	-	-	A1 (96/603/EC)
<b>Roofing materials</b>							
	Flexible sheet for waterproofing - Bitumen	EN 13707 <sup>3)</sup>	2.5-5.0	-	-	-	B <sub>ROOF</sub> (t2) (EN 13707)
	Flexible sheet for waterproofing - PVC	EN 13956 <sup>3)</sup>	1.6	-	-	-	B <sub>ROOF</sub> (t2) (EN 13956)
<b>Windows and external doors</b>							
	Windows and external doors	EN 14351-1	U <sub>w</sub> ≤ 1,4 [W/m <sup>2</sup> K]			R <sub>w</sub> ≥ 35 [dB]	DoP
	Internal doors	EN 14351-2	-			-	-

- 1) Various ETAs; ETA number is specified in the quality system of "Kodumaja building modules". ETA is only valid if it accompanied by CPR-certificate issued based on the same ETA.
- 2) The products that have a SINTEF Technical Approval, are assessed and approved in accordance with provisions in EAD 030352-00-0503 Watertight covering kits for wet room floors and/or walls and may be used. The valid approvals may be found at <https://www.sintefcertification.no> and are specified in the quality system of "Kodumaja building modules"
- 3) The products shall be classified as watertight in accordance with relevant harmonised standard (EN) and have valid CPR certificate, or valid SINTEF Technical approval (<https://www.sintefcertification.no/Contents/Index/3>)

Table A2-2 – Corrosion protection of fasteners used in "Kodumaja building modules".

Product	Technical specification	Main dimensions (mm)	Corrosion protection (Service class)
Staples	EN 14592+A1	See Annex 1	Service class 1, 2
Corrugated staples	EN 14592+A1, ETA based on EAD 130033-00-0603*	See Annex 1	Service class 1, 2
Screws	EN 14592+A1, ETA based on EAD 130033-00-0603*	See Annex 1	Service class 1, 2 (3 outdoor)
Screws (gypsum board)	EN 14566+A1	See Annex 1	Service class 1, 2
Nails	EN 14592+A1, ETA based on EAD 130033-00-0603*	See Annex 1	Service class 1, 2 (3 outdoor)
Connectors / Punched metal plate fasteners	EN 14545	According to pre-defined solutions / structural calculation	Service class 1, 2
Three-dimensional nailing plates (joist hangers, hold downs, angle brackets)	ETA based on ETAG 015 used as EAD and EAD 130186-00-0603*	According to pre-defined solutions / structural calculation	Service class 1, 2

\*Various ETAs; ETA number is specified in the quality system of "Kodumaja building modules".

## Annex A3 – Resistance to fire

The fire resistance for the building components are given in Table A3-1 and A3-2. The fire resistance is determined by tests, and by calculations according to the manual *Brandsäkra Trähus version 3* and EN 1995-1-2.

Design load capacity for limit state fire is given by maximum centric axial load per meter wall (kN/m with c/c 600 mm between the studs). Design load capacity for limit state fire for single spanned floors and roof is given by maximum bending moment (kNm) per beam. "No reduction" means that board materials protect structural timber components from charring during the fire exposure period, and the design capacity determined for ultimate and serviceability limit states can be applied.

Table A3-1

For basic module designs as shown in the Annex A1, the resistance to fire classified according to EN 13501-2 is as follows for fire exposure from the inside on external walls, one-sided on internal walls and from below on separating floors and roofs. The drawings are shown in Annex A1.

<b>Structure</b>	<b>Fire resistance<sup>1)</sup></b>	<b>Design load capacity<sup>2)</sup></b>
<b>External walls</b> – shown in Annex A1, drawing EW-01, EW-01-W, EW-02, EW-02-W, EW-03, EW-03-W - with 2 layers of 12.5 mm gypsum board type A lining - wall height ≤ 2,6 m	<b>REI 30</b>	<b>Full capacity</b>
<b>External walls</b> – shown in Annex A1, drawing EW-01, EW-01-W, EW-02, EW-02-W, EW-03, EW-03-W - with 2 layers of 12.5 mm gypsum board type F lining - wall height ≤ 2,6 m	<b>REI 60</b>	<b>117 kN/m</b>
<b>Internal separating walls – load-bearing</b> – shown in Annex A1, drawing PW—01, PW—01-W - with 2 layers of 12.5 mm gypsum board type A lining - wall height ≤ 2,6 m	<b>REI 30</b>	<b>Full capacity</b>
<b>Internal separating walls – load-bearing</b> – shown in Annex A1, drawing PW—01, PW—01-W - with 2 layers of 12.5 mm gypsum board type F lining - wall height ≤ 2,6 m	<b>REI 60</b>	<b>17 kN/m</b>
<b>Shaft walls not load-bearing, one sided fire</b> - shown in Annex A1, drawing IW-01, IW-01-W - with one layer of 12.5 mm gypsum board type A lining on each side and 70 mm mineral wool - wall height ≤ 2,6 m	<b>EI 30</b>	-
<b>Shaft walls not load-bearing, one sided fire</b> - shown in Annex A1, drawing IW-01, IW-01-W - with 2 layers of 12.5 mm gypsum board type A lining on each side and 70 mm stone wool - wall height ≤ 2,6 m	<b>EI 60</b>	-
<b>Separating floors</b> – shown in Annex A1, drawing CE-01, CE-02 - with 2 layers of 12.5 mm gypsum board type A as ceiling	<b>REI 30</b>	<b>Full capacity</b>
<b>Separating floors</b> – shown in Annex A1, drawing CE-01, CE-02 - with 2 layers of 15 mm type F gypsum board as ceiling	<b>REI 60</b>	<b>Full capacity</b>
<b>Roof</b> – shown in Annex A1, drawing RE-01, RE-02 - with 2 layers of 12.5 mm gypsum board type A as ceiling	<b>R 30</b>	<b>Full capacity</b>
<b>Roof</b> – shown in Annex A1, drawing RE-01, RE-02 - with 2 layers of 15 mm type F gypsum board as ceiling	<b>R 60</b>	<b>Full capacity</b>

<sup>1)</sup> Fire resistance equivalent to classification according to EN 13501-2. The fire resistance for separating (EI) and load bearing (R) elements in minutes.

<sup>2)</sup> Vertical design load capacity at accidental limit state in case of fire. "Full capacity" means no reduction in capacities determined at limit state fire.

Table A3-2

For alternative module designs as shown in Annex B, the resistance to fire classified according to EN 13501-2 is as follows for fire exposure one-sided on internal walls and from below on separating floors. The loadbearing capacities of structures for action fire are calculated according to EN 1995-1-2 for each individual kit and delivery.

<b>Structure</b>	<b>Fire resistance<sup>1)</sup></b>
<b>Internal separating walls – load-bearing (see Annex B)</b> - confidential information	<b>REI 90</b>
<b>Separating floors – load-bearing (see Annex B)</b> - confidential information	<b>REI 120</b>

<sup>1)</sup> Fire resistance equivalent to classification according to EN 13501-2. The fire resistance for separating (EI) and load bearing (R) elements in minutes.

<sup>2)</sup> Vertical design load capacity at accidental limit state in case of fire. "Full capacity" means no reduction in capacities determined at limit state fire.